

www.UltraGard.com.au

PERFORMANCE DATA




Extreme protection from the Australian sun

On 3mm clear glass

Product Code	MX15
Film Thickness	2.0 mil
Film Roll Sizes	72" / 60" / 48" / 36" / 24"
Adhesive Chemistry	(Dry) Water Activated
Release Liner Construction	(BOPP) Polypropylene
Total Solar Energy Rejected (T.S.E.R.)	70 %
Visible Light Transmitted (V.L.T.)	16 %
Visible Light Reflected - Interior/Exterior	12 % / 18 %
Solar Energy Reflected	19 %
Solar Energy Transmitted	12 %
Solar Energy Absorbed	69 %
Visible Glare Reduction	84 %
Ultraviolet Protection	99 %
Fading Reduction Estimate	79 %
Shading Coefficient (S.C.)	0.35
Solar Heat Gain Coefficient (S.H.C.G.)	0.30
Winter U-Value (W/M ² K)	5.79
Emissivity (Room side)	0.79
Luminous Efficacy	0.46
Daytime Privacy Rating	High
Warranty	Lifetime Residential / 12 Year Commercial

CARBON BLACK
Residential & Commercial
Glass Window Film

MX15



www.UltraGard.com.au

PERFORMANCE DATA




Extreme protection from the Australian sun

On 3mm clear glass

Product Code	MX24
Film Thickness	2.0 mil
Film Roll Sizes	72" / 60" / 48" / 36" / 24"
Adhesive Chemistry	(Dry) Water Activated
Release Liner Construction	(BOPP) Polypropylene
Total Solar Energy Rejected (T.S.E.R.)	65 %
Visible Light Transmitted (V.L.T.)	23 %
Visible Light Reflected - Interior/Exterior	13 % / 15 %
Solar Energy Reflected	16 %
Solar Energy Transmitted	16 %
Solar Energy Absorbed	68 %
Visible Glare Reduction	76 %
Ultraviolet Protection	99 %
Fading Reduction Estimate	75 %
Shading Coefficient (S.C.)	0.41
Solar Heat Gain Coefficient (S.H.C.G.)	0.35
Winter U-Value (W/M ² K)	6.02
Emissivity (Room side)	0.75
Luminous Efficacy	0.56
Daytime Privacy Rating	Medium
Warranty	Lifetime Residential / 12 Year Commercial

CARBON BLACK
Residential & Commercial
Glass Window Film

MX24



www.UltraGard.com.au

PERFORMANCE DATA



Extreme protection from the Australian sun

On 3mm clear glass

Product Code	MX43
Film Thickness	2.0 mil
Film Roll Sizes	72" / 60" / 48" / 36" / 24"
Adhesive Chemistry	(Dry) Water Activated
Release Liner Construction	(BOPP) Polypropylene
Total Solar Energy Rejected (T.S.E.R.)	50 %
Visible Light Transmitted (V.L.T.)	45 %
Visible Light Reflected - Interior/Exterior	13 % / 15 %
Solar Energy Reflected	14 %
Solar Energy Transmitted	36 %
Solar Energy Absorbed	50 %
Visible Glare Reduction	51 %
Ultraviolet Protection	99 %
Fading Reduction Estimate	67 %
Shading Coefficient (S.C.)	0.57
Solar Heat Gain Coefficient (S.H.C.G.)	0.50
Winter U-Value (W/M ² K)	6.08
Emissivity (Room side)	0.75
Luminous Efficacy	0.88
Daytime Privacy Rating	Low
Warranty	Lifetime Residential / 12 Year Commercial

CARBON BLACK
Residential & Commercial
Glass Window Film

MX43