



## TTT-ENM-12

### 1 DESCRIPTION

TTT-ENM-12 is manufactured to conform with the requirements of Military Specification MIL-1-16411 Type II, ASTM-C-1086-96 and Coast Guard Specification for Incombustible Materials #164.009 and MIL-1-24244. TTT-ENM-12 is a fiberglass mat composed of 100% "E" type glass fibers 9-13 microns in diameter which are put into web form and mechanically needled together without chemical binders.

### 2 APPLICATIONS

TTT-ENM-25 is intended for use as a thermal insulation and gasket material in home and industrial furnaces, package boiler and for special piping applications where heat resistance, exibility and low special air and liquid chemical and thermal resistance are mandatory.

### 3 ADVANTAGES

The unique properties of TTT-ENM-12 make it an effective low cost replacement for asbestos mats, millboard, ceramic or refractory paper, mat and sheets and mineral boards.

### 4 PROPERTY DATA

Characteristics:	Method:	English Values:	Metric Values:
Weight		6 oz/sqft	1831.2 g/m <sup>2</sup>
Thickness	ASTM-D-1777	1/2" +/- 10%	25.4 mm +/- 10%
Density		9 lbs/ft <sup>3</sup>	144.2 kg/m <sup>3</sup>
Temperature Resistance	N/A	Max: 1200°F	Max: 649°C
Flame Resistance	ASTM-E-84	Flame Spread: 0 Smoke Developed: 0	
Tensile Strength	N/A	Machine: 80 lbs Cross machine: 60 lbs	Machine: 36.2874 kg Cross machine: 27.2155 kg
Acoustical Ratings	N/A	250 frequency: .07 +/- .02 500 frequency: .24 +/- .1 1000 frequency: .55 +/- .01 2000 frequency: .49 +/- .02 4000 frequency: .91 +/- .02	
Color:	N/A	White	

\*\*\*All values are nominal unless otherwise specified. All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.