



SILICA FABRIC

TESTING FOR: FLAME RESISTANCE

TEST METHOD: FOLD

| | |
|---------------------|-------------|
| After Flame: | 0.0 seconds |
| (Requirement: 2 | 0.0 seconds |
| max individual) | 0.0 seconds |
| | 0.0 seconds |
| Average: | 0.0 seconds |

| | |
|---------------------|------------|
| Char Length: | 0.2 inches |
| (Requirement: 41.3 | 0.2 inches |
| max individual) | 0.3 inches |
| | 0.2 inches |
| Average: | 0.2 inches |

| | |
|---------------------|-------------|
| Dripping and | 0.0 seconds |
| Flaming: | 0.0 seconds |
| (Requirement: 2 | 0.0 seconds |
| max individual) | 0.0 seconds |
| Average: | 0.0 seconds |