



RUBBER COATED FIBERGLASS FABRIC

TESTING FOR: FLAME RESISTANCE

TEST METHOD: FOLD

After Flame:	0.0 seconds
(Requirement: 2	0.0 seconds
max individual)	0.0 seconds
	0.0 seconds
Average:	0.0 seconds

Char Length:	0.9 inches
(Requirement: 41.3	0.1 inches
max individual)	0.5 inches
	0.4 inches
Average:	0.5 inches

Dripping and	0.0 seconds
Flaming:	0.0 seconds
(Requirement: 2	0.0 seconds
max individual)	0.0 seconds
Average:	0.0 seconds