

INTERIOR LOW SHEEN

LINE 4686
FEBRUARY 2014
PAGE 1 OF 3



Description & Uses

Tradesman Interior Low Sheen White is an economical water based interior wall paint.

Colours

Colours available tinted from white base. This product is slightly shaded and therefore tinted colours may appear slightly darker than the standard colour.

Low Sheen (Gloss level 5 - 10 at 60 degrees)

Properties & Performance Guide

Dry & Recoat Times	Surface Dry - 30 minutes Recoat - 2 hours Fully Cured - 7 days Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.
Coverage per Coat	Up to 14 M ² /L depending on the surface texture, porosity and method of application.
Film Thickness	Wet Film Thickness (WFT) - 75 microns minimum Dry Film Thickness (DFT) - 25 microns minimum
Thinning	Thinning is generally not required. If necessary to aid spray atomisation, thin with up to 5% water.
Clean Up	Clean up with cold water away from drains. Protect Our Environment: Do not pour leftover paint down the drain. Unwanted paint should be kept in a sealed container, and then disposed of via special waste collection services. Empty paint containers should be left open in a well ventilated area to dry out. Disposal of empty paint containers may differ between local authorities. Check with your local council first.

INTERIOR LOW SHEEN

LINE 4686
FEBRUARY 2014
PAGE 2 OF 3

Recommended Substrate Conditions & Preparation

Surfaces are to be suitably prepared in accordance with proper trade practices.

Ensure the surface is clean, dry and free from dust, dirt and grease. All loose, peeling or flaking material must be removed. Uneven surfaces should be sanded smooth with fine abrasive paper and all dust removed. Sand enamel painted surfaces to remove gloss. Fill holes and cracks with a suitable filler and sand lightly to an even finish. All new cement surfaces need to be fully cured (typically 4 – 6 weeks) prior to painting. Ensure surfaces are free of bond breakers, formwork release agents and curing compounds. Test soundness of previously painted surfaces before painting. Unsound surfaces should be stripped before repainting.

Previously painted surfaces, plasterboard, unpainted brick, cement render, fibre cement or masonry

Apply one coat of Solver Trade Acrylic Sealer Undercoat (Line 4702).

New Paper-faced plasterboard

Apply one coat of Tradesman Gypseal.

Interior bare timber and MDF

Apply one coat of Solver Trade Acrylic Sealer Undercoat (Line 4702). For tannin rich timber first apply one coat of Solver Ultra Primer Sealer Undercoat (Line 4320).

New set plaster

Apply one coat of Solver Wall-Sealer (Line 4129) or Solver Preps Acrylic Plaster Sealer (Line 4360).

Mould & Fungus Infected Areas

Clean surface with household bleach then rinse well with clean water and allow to dry. Treat the surface with Solver Sterilizing Wall-Wash (Line 4651). If abnormal conditions are expected e.g. condensation, dampness etc, Solver Anti-Fungus Additive No. 1 (Line 4651) may be added to the paint for extra protection. For normal conditions this addition will not be necessary.

Application Guide

Stir well before and during use with a broad paddle reaching to the bottom of the can and using an upward lifting action.

Apply two full, even coats by brush, roller or airless spray.

Use a medium nap (12mm pile) synthetic roller on smooth and semi-smooth surfaces.

Use a longer nap (20mm pile) synthetic roller on rough surfaces, e.g. Besser Block.

Use a 13 or 15 thou Tip for airless spray.

Do not apply when temperature is below 10°C or above 35°C or when humidity is very high.

Additional Data

Available in 10 and 15 litres.

If the paint has been tinted, check that the colour is suitable for your requirements before application. For best results and colour consistency, tinted paint should be boxed and thoroughly mixed on site.

Avoid exposure to steam and condensation for 48 hours after application of final coat.

Containers must be secured and stored upright during transit.

Containers must not be exposed to excessive heat or cold.

The use of proprietary additives other than those manufactured by Valspar is not recommended.

Do not use for any other purpose other than as specified in our literature.

INTERIOR LOW SHEEN

LINE 4686
FEBRUARY 2014
PAGE 3 OF 3

Safety Data	
First Aid Instructions	For advice, contact the Poisons Information Centre on 131 126 (Aust) or a doctor. If swallowed, do not induce vomiting. Give a glass of water to drink. If in eyes, wash out immediately with water. If inhaled remove from contaminated area to fresh air. If skin contact occurs, remove contaminated clothing and flush contaminated skin with water.
Safety Directions	Keep out of reach of children. Avoid contact with skin and eyes. Ensure adequate ventilation during use. Avoid prolonged breathing of vapour. Wash hands thoroughly after use.
Further Information	For further information contact the Valspar Customer Care Hotline on 132 101.

1. This information is provided with respect to the listed products. Valspar (WPC) recommends that:

(a) You review the Technical Data Sheets (TDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Valspar; (c) the product be transported and handled in accordance with the SDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in the technical data sheet was prepared using information gathered during product development. While Valspar endeavours to update this information and maintain the accuracy of its contents, Valspar cannot guarantee that the information is wholly comprehensive.

3. Valspar recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Valspar Office.

4. To the full extent permitted by law, Valspar's liability for breach of a condition or warranty implied into the contract for sale between Valspar and you by law is limited at Valspar's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

Solver, Solver Trade & Solver Ultra are registered trademarks of Valspar (WPC) Pty Ltd ABN 65 007 527 371.

INFORMATION HOTLINE: Ph: 132 101 (AUSTRALIA)