

TECHNICAL DATA SHEET

ANULON 98



Material Characteristics

- High resistance to chemicals
- Resistance against low temperature (-40°C)
- High strength

Property	Unit	Test Method	Value
Specific Gravity	g/cm ²	ASTM D792	0.941-0.965
Tensile strength	Kg/cm ²	ASTM D638	218-387
Compressive strength	Kg/cm ²	ASTM D695	169
Impact strength	Kg cm/cm ²		no break
Elongation at break	%	ASTM D651	50-600
Shore Hardness	Shore D	ASTM D2240	60-70
Water absorption	%	ASTM D570	<0.01
Melting Point	°C	ASTM D3702	165
Flammability		ASTM D635	very slow
Dielectric strength	Volts/mm	ASTM D149	>800

PLASTIC ABHIYANTA

PLASTIC ENGINEERS & CONSULTANTS

AN ISO 9001:2015 CERTIFIED COMPANY

 25A, CHANDNI CHOWK STREET, 1st FLOOR,
KOLKATA-700072, INDIA
 anulon@plasticabhiyanta.com
 +91 8240692783

www.anulon.com

All the given information is given above in good faith but without any guarantee