

description Uncoated papers and boards made with E.C.F. pulp. Felt marked on both sides. Pulp-dyed with light-fast colours. Available in seventeen shades.

range	size	grain	substa		
	70x100	LG	190	260	360

technical features	substance	VSA	Wax pick test	Taber stiffness 15° ISO 2493	
ref. standard/instrument	ISO 536	ISO 534	UNI 9073		
unit of measure	g/m²	cm ³ /g	n° (Dennison)	mN	
				long±10%	trasv±10%
	190 ± 4%	1,45	≥ 14	80	40
	260 ± 5%	1,45	≥ 14	190	100
	360 ± 5%	1,45	≥ 14	500	230

Brightness (col. Bianco) ISO 2470 (R457) - 91% ± 2 Relative Humidity 50% ± 5 ref. TAPPI 502-98



notes

The products could show light differences in papershade and look due to natural raw materials used. The product is completely biodegradable and recyclable. Special runs available upon request.

Fabriano is a trademark of Fedrigoni SpA The Company reserves the right to modify the technological features of the product in relation to market requirements.

UNI EN ISO 9001:2008 - CQ 539 UNI EN ISO 14001:2004 - CQ 7847 BSI - OHSAS 18001:2007 - CQ 15229



Product Data Sheet MAR/660 Update 07/2012 Rev. nº 01 Murillo papers and boards are ideal for any kind of publishing, packaging and commercial printing. They are held in high regard for packaging, special publications, brochures, booklets, greeting-cards and coordinated graphic materials.

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. The characteristic felt marking requires specific printing pressure settings. The Black shade, is made without the use of Carbon Black pigment. Are excluded oxidation problems or mottling for the hot foil stamping.

Varnishing and plastic laminating must be assessed in advance. The varnishing coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of felt marked papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing. printing suggestions

applications

converting suggestions

FABRIANO