



TEST REPORT

ISSUED BY **British Board of Agrément**
DATE OF ISSUE **18 February 2016**
SERIAL NUMBER **55209THAAN**



REPORT PREPARED BY

E Whyte
Senior Test Technician

Bucknalls Lane, Garston
Watford, Herts WD25 9BA
Tel: 01923 665300
Fax: 01923 665301
e-mail: testing@bba.star.co.uk
<http://www.bbacerts.co.uk>

©British Board of Agrément 2016

AUTHORISED BY

S Sadler
Head of Test

CLIENT: MMB Developments Ltd
Bridgend Industrial Estate
Unit 8 Gartferry Road
Moodiesburn
North Lanarkshire
G69 0JD

JOB No: T955209

1 INTRODUCTION

The test specimen was produced by the client at the BBA on 23 November 2015 and described as Retrofoam 50 mm thickness urea formaldehyde foam cavity insulation, batch number 2300013673, foaming agent catalyst batch number C978401. The foam was sprayed into a 600 mm x 600 mm x 50 mm mould. Due to the freshly sprayed foam being very fragile the sample was stored in the mould for one week until it was firm enough to remove it without damage.

2 METHOD

Heat Flow Meter Method of ISO 8301 : 1991 and BS EN 12667 : 2001 using the BBA single specimen symmetric test facility designated K5.

Specimen thickness was measured in accordance with BS EN 12667 : 2001.

3 SPECIMEN PREPARATION

The test specimen was assigned the BBA designation number S255057/1 and stored in a well-ventilated position in an air-conditioned room at $23 \pm 2^\circ\text{C}$, $50 \pm 5\%$ RH until it had dried and constant mass was achieved. A normality specimen with dimensions 400 mm x 400 mm x 20 mm was prepared and tested immediately after cutting. The specimen was then aged at 70°C for 21 ± 1 days and tested, the aged normality results are contained in this report.

4 MEASURED PROPERTIES

Thermal conductivity W/(m·K)	Thermal resistance m ² ·K/W	Density kg/m ³	Mean temperature (°C)
0.0294 ± 2.5%	0.684 ± 2.5%	22	10.2

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025:2005.

This report provides traceability of measurement to recognised national standards, and to the units of measurement realised at the National Physical Laboratory or other recognised national standards laboratories. This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

TEST REPORT

UKAS ACCREDITED TESTING LABORATORY No 0357

SERIAL NUMBER **55209THAAN**

5 RESULTS

Test details

Relative mass change during conditioning	-0.40%
Cold face temperature	0.2°C
Hot face temperature	20.2°C
Average temperature difference across specimen	20.0 K
Relative mass change during test	0.03%
Average imposed specimen thickness	20.1 mm
Mean heat flux	29.3 W/m ²
Direction of heat flux	Upwards
Interface medium	None
Applied load	8.8 kPa
Cold face emissivity	0.89
Hot face emissivity	0.89
Duration of test (hh:mm)	1:53
Duration of steady state (hh:mm)	1:30
Date of test completion	18 February 2016
Angle of orientation	0°

Calibration details

Date of last verification

Feb-16

Certified reference material

Type: Resin Bonded Glass Fibre Board, Ref: IRMM-440,
Cal Date: 23 Dec 2008

6 COMMENTS

This report refers to the aged result for the normality specimen, see BBA test report numbered 55209THAIN for the initial normality results.

TEST REPORT

UKAS ACCREDITED TESTING LABORATORY No 0357

SERIAL NUMBER **55209THAAN**

7 REPORT CONDITIONS

7.1 This Report:

- relates only to the product/system and sample/specimen thereof named and described herein
- relates only to the specified tests and test conditions described herein
- is issued only to the company, firm, organisation or person named herein — no other company, firm, organisation or person may hold this Report or claim that it has been issued to them
- has to be read, considered and used as a whole document — it may be misleading and will be incomplete to be selective
- is copyright of the BBA
- is subject to English Law.

7.2 No verification of any of the materials, samples, specimens, information, data or documents supplied to the BBA has been made, except where otherwise stated.

7.3 Publications, documents, specifications and similar matter that are referred to herein, are those that were current at the date of issue of this Report, except where otherwise stated.

7.4 The BBA has used due skill, care and diligence in preparing this Report, but no warranty is given or implied.

7.5 In issuing this Report, the BBA is not responsible; and is excluded from any liability to any company, firm, organisation or person; for any matters arising directly or indirectly from:

- the presence or absence of any patent, intellectual property or similar rights subsisting in the product/system
- individual installations of the product/system, including their nature, design, methods, performance, workmanship and maintenance
- any works and constructions in which the product/system is installed, including their nature, design, methods, performance, workmanship and maintenance
- any loss or damage, including personal injury, howsoever caused by the product/system, including its manufacture, supply, installation, use, maintenance and removal.

7.6 This Report does not constitute or indicate any approval, certification or endorsement of the product/system.