

**NVLAP Bulk Asbestos Proficiency Test
M22025 - December 19, 2025
Individual Laboratory Results**

NVLAP Lab Code 901054

California Asbestos Laboratory LLC
1440 S State College Blvd.
Suite 4E
Anaheim, CA 92806
United States

PROFICIENCY TEST PENALTY POINTS

Sample 1	0
Sample 2	0
Sample 3	0
Sample 4	0
Other *	0
TOTAL POINTS:	0

Failure = 150 or more total points

* Penalty points are assigned for failure to follow instructions. Additional details (if any) for error points assigned are listed below:

Prepared by RTI International for
Participants in NIST's National Voluntary Laboratory Accreditation Program
For Bulk Asbestos Analysis by PLM

NVLAP Bulk Asbestos Proficiency Test
M22025 - December 19, 2025
Individual Laboratory Results

NVLAP Lab Code 901054

Sample 1

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Pos > 0.1 % (150 pts.) False Pos = 0.1 % (75 pts.)	NONE	None	None	

Total Points Assigned for Sample 1: 0

NVLAP Bulk Asbestos Proficiency Test

M22025 - December 19, 2025

Individual Laboratory Results

NVLAP Lab Code 901054

Sample 2

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	CROC	Crocidolite	Crocidolite	
% Asbestos (50 pts.)	8	5.4 %	1.0 % to 10.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.698$ $\gamma = 1.702$	$\alpha = 1.692$ $\gamma = 1.699$	α : 1.682 to 1.702 γ : 1.691 to 1.707	
Birefringence (10 pts.) *	L	Low	Low or Moderate *	
Pleochroism (10 pts.)	Y	Yes	Yes	
Extinction (10 pts.)	P	Parallel	Parallel	
Sign of Elongation (10 pts.)	N	Negative	Negative	
Color (10 pts.)	BL	Blue	Blue	
Reporting Additional Asbestos Type (75 pts.)		None	None	

* Birefringence results must be correctly calculated based on participant measured refractive index values.

Total Points Assigned for Sample 2: 0

NVLAP Bulk Asbestos Proficiency Test

M22025 - December 19, 2025

Individual Laboratory Results

NVLAP Lab Code 901054

Sample 3

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	CHRY	Chrysotile	Chrysotile	
% Asbestos (50 pts.)	5	3.3 %	0.1 % to 7.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.550$ $\gamma = 1.557$	$\alpha = 1.547$ $\gamma = 1.554$	α : 1.542 to 1.552 γ : 1.550 to 1.558	
Birefringence (10 pts.) *	L	Low	Low or Moderate *	
Pleochroism (10 pts.)	N	No	No	
Extinction (10 pts.)	P	Parallel	Parallel	
Sign of Elongation (10 pts.)	P	Positive	Positive	
Color (10 pts.)	CL	Colorless	Colorless	
Reporting Additional Asbestos Type (75 pts.)		None	None	

* Birefringence results must be correctly calculated based on participant measured refractive index values.

Total Points Assigned for Sample 3: 0

NVLAP Bulk Asbestos Proficiency Test

M22025 - December 19, 2025

Individual Laboratory Results

NVLAP Lab Code 901054

Sample 4 – Type 1

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	AMOS	Amosite	Amosite	
% Asbestos (50 pts.)	10	7.1 %	0.1 % to 14.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.682$ $\gamma = 1.698$	$\alpha = 1.678$ $\gamma = 1.700$	α : 1.673 to 1.683 γ : 1.694 to 1.706	
Birefringence (10 pts.) *	M	Moderate	Low or Moderate *	
Pleochroism (10 pts.)	N	Yes	Yes or No	
Extinction (10 pts.)	P	Parallel	Parallel	
Sign of Elongation (10 pts.)	P	Positive	Positive	
Color (10 pts.)	CL	Colorless	Colorless, Brown	
Reporting Additional Asbestos Type (75 pts.)	CHRY 6 %	Chrysotile	Chrysotile	

* Birefringence results must be correctly calculated based on participant measured refractive index values.

NVLAP Bulk Asbestos Proficiency Test

M22025 - December 19, 2025

Individual Laboratory Results

NVLAP Lab Code 901054

Sample 4 – Type 2

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	CHRY	Chrysotile	Chrysotile	
% Asbestos (50 pts.)	6	1.1 %	0.1 % to 10.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.549$ $\gamma = 1.549$	$\alpha = 1.549$ $\gamma = 1.556$	α : 1.546 to 1.552 γ : 1.551 to 1.561	
Birefringence (10 pts.) *	L	Low	Low or Moderate *	
Pleochroism (10 pts.)	N	No	No	
Extinction (10 pts.)	P	Parallel	Parallel	
Sign of Elongation (10 pts.)	P	Positive	Positive	
Color (10 pts.)	CL	Colorless	Colorless	
Reporting Additional Asbestos Type (75 pts.)	AMOS 10 %	Amosite	Amosite	0

* Birefringence results must be correctly calculated based on participant measured refractive index values.

Total Points Assigned for Sample 4: 0

NVLAP Laboratory Contacts

NVLAP Lab Code 901054

California Asbestos Laboratory LLC

Please review your contact information below and make sure it is accurate. If there are any changes, please update your information on the RTI website, <https://nvlap-plm.rti.org/>.

Also, NVLAP no longer sends the NVLAP Authorized Contact list to RTI at the start of each round. When your NVLAP Authorized Representative changes, please contact NVLAP, nvlap@nist.org, and update your primary contact information on the RTI website.

Laboratory Primary Contact (NVLAP Authorized Contact)

Anthony Reyes

Email: anthony@calilabtesting.com

Phone: 949-886-7328

Laboratory / Shipping Contact

Anthony Reyes

1440 S State College Blvd.

Suite 4E

Anaheim, CA 92806

United States

Email: anthony@calilabtesting.com

Phone: 949-886-7328

Laboratory Billing Contact

Anthony Reyes

Email: anthony@calilabtesting.com

Phone: 949-886-7328

Thank you for participating in the NVLAP Bulk (PLM) Proficiency Testing Program.