Edition 24/08/2005 Identification no: 02 05 02 01 002 0 System SikaTack®-Panel System

SikaTack®-Panel System

The panel fixing system for ventilated façades

System Description	The SikaTack [®] -Panel System is an adhesive system for the economic, concealed fixing of ventilated façade panels. The system consists of the elastic adhesive SikaTack [®] -Panel, the double sided SikaTack [®] -Panel fixing tape and pre-treatment products. With the SikaTack [®] -Panel						
Uses	System, façade panels are invisibly attached to their normal substructures. Concealed bonded fixing of ventilated façade panels for:						
	Residential and commercial buildings						
	 New build and renovation projects 						
	Interior finishing works						
Characteristics / Advantages	 1-part products, ready to use Economical for rapid fixing Uniform tension over the whole façade panel (no stress points) Resistant to weathering and ageing Vibration and movement absorbing fixing system Provides creative opportunities for façade design Good looking, easy to maintain façade surface Silicone free 						
Tests							
Approval / Standards	Approval from "Deutsches Institut für Bautechnik" Berlin, Reg. No.: Z-36.4-18.						
	Note: Panels have to be pre-tested to confirm their suitability.						

Our Technical Department can assist in this evaluation.



Product								
Description	SikaTack [®] -Panel Adhesive							
Uses	1-part adhesive for the SikaTack®-Panel System.							
Product Data								
Form								
Colour	lvory							
Packaging	310 ml cartridges, 12 cartridges per box. 600 ml unipacs, 20 sausages per box.							
Storage								
Storage Conditions / Shelf Life	9 months from date of production if stored properly in undamaged original sealed containers in dry conditions and protected from direct sunlight at temperatures between +10°C and +25°C.							
Technical Data								
Chemical Base	1-part polyurethane, moisture curing.							
Density	1.18 kg/l (DIN 53 479)							
Skinning- / Laying Time	20 min. (+23° C / 50r. h.)							
Curing Rate	4 mm / 24h (+23°C / 50 r. h.)							
Service Temperature	-40°C to +90°C							
Building-Material Class	B2 DIN 4102 part 1							
Mechanical / Physical Properties								
Shear Strength	~ 2.00 Mpa							
Tensile Strength	~ 2.50 Mpa							
System Information								
Application Conditions / Limitations								
Ambient Temperature	+5°C min. / +35°C max.							

Product Description	SikaTack [®] Products for Panel Pre-treatment						
Uses	Cleaning and bonding agents to optimise adhesion.						
Product Data							
Form	Sika [®] Cleaner-205	SikaTack [®] -Panel Primer					
Colours	Clear, colourless	Black					
Packaging	4 bottles with 1000 ml content 6 bottles with 250 ml content	4 bottles with 1000 ml content					
Storage	Sika [®] Cleaner-205	SikaTack [®] -Panel Primer					
Storage Conditions / Shelf -Life	From date of production if stored in undamaged original sealed containers, in dry conditions and protected from direct sunlight at temperatures between +10°C and 25°C.						
	12 months	9 months					
Technical Data	Sika [®] Cleaner-205	SikaTack [®] -Panel Primer					
Chemical Base	Bonding agent in alcohol solution.	Solvent containing pigmented epoxy resin					
Density	0.80 kg/l	1.00 kg/l					
Flash Point	+14°C	-4°C					
System Information							
Application Conditions / Limitations							
Ambient Temperature	+5°C min. / +35°C max.	+5°C min. / +35°C max.					

Product								
Description	SikaTack [®] -Panel Fixing Tape							
Uses	A double sided self adhesive fixing tape used for the initial fixing of façade panels (until the adhesive has cured and also to ensure that the minimum thickness of the SikaTack®-Panel adhesive is 3 mm.							
Product Data								
Form								
Colour	Anthracite							
Packaging	33 m per roll, 25 rolls per box							
Storage								
Storage Conditions / Shelf life	24 months from date of production if stored properly in undamaged original sealed containers in dry conditions and protected from direct sunlight at temperatures between +10°C and +25°C.							
Technical Data								
Chemical Base	Closed cell polyethylene foam.							
Density	0.064 kg / l (DIN 51 757)							
Thickness	12 mm							
Dimension	3.3 mm (<u>+</u> 0.2 mm)							
Service Temperature	-40°C to +70°C							
Mechanical / Physical Properties								
Compressive Strength								
	Deflection	Compressive strength (ISO 844)						
	10%	22 kPa						
	25%	47 kPa						
	50%	120 kPa						
Shear Strength	> 150 hours (1 kg / 25 x 25 mm)	(FTM 2)						
Tensile Strength	MD 25 N / 15 mm, CD 20 N / 15 mm	(DIN 53 455)						
Elongation at Break	MD 250%, CD 150%	(DIN 53 455)						
Peel Strength	> 23 N / 25 mm (180°C - 30 min.) on stai	nless steel (FTM 1)						
Important	Long-term strength is provided by the SikaTack-Panel adhesive. Do not include the mechanical values of the tape in the calculation of the long term strength required. The tape must be applied onto the full length of the substructure.							
System Information								
Application Conditions / Limitations								
Ambient Temperature	+10°C min. / +35°C max.							

System Information

System Structure

Aluminium substructure:

The substructure must be approved by the construction supervisery authority (L, T or H shapes or equivalent) consisting at least of the alloy AIMgSi 0.5 F 22 in accordance with DIN 1748-1.

Timber substructure:


Perpendicular battens made of spruce or pine, planed, smooth and with a max. moisture content of the wood < 14% in accordance with DIN 1052. The adhesive area must be untreated. The joints between the individual battens must be at least 1 cm wide.

Design and dimensions:

The dimensions of the perpendicular substructure depends on the façade construction. The distances between the substructure battens and their width are determined by the load requirements and by the type of panel used.

Each project requires specific design detailing.

Examples



Required width of substructure battens for the use of the SikaTack®-Panel System.

The full height of the façade panel must be bonded.

Calculated permissible values of load bearing capacity:

Width of adhesive: 10 mmTensile stress: ~ 0.15 Mpa

- Shear stress: ~ 0.12 Mpa (permissible reduction factor S = 1.0)

Movement joints:

For the correct design and dimensioning of the system and for correct anchoring of the vertical aluminium or timber substructure, all standard building regulations for cladding apply.

The vertical aluminium or wooden battens must be parallel and even in order to ensure uniform, stress free adhesion of the cladding panels. Joints in the substructure must not be bonded over by panels. The distances between the panels at joints must be sufficiently wide to avoid compression of the panels due to thermal movement. The data of the panel manufacturer are to be compiled with expansion coefficient of the substructure. Sufficiently large openings for ventilation must be provided at the top and bottom of the system.

Note: These system configurations must be fully complied with as described and details and may not be changed.

Application Details Consumption / Dosage Material Application Consumption SikaTack®-Panel ~ 44 ml / m¹, corresponds to Triangular bead 7 m¹ / cartridge Cartridge 310 ml 8 x 10mm Unipac 600 ml or 13 m¹ / unipac Sika® Cleaner-205 ~ 3.5ml / m¹, corresponds 250 ml bottle Width 50 mm to $\sim 71 \text{ m}^1 / 250 \text{ ml bottle}$ 1000 ml bottle to ~285 m¹ / 1000 ml bottle SikaTack®-Panel Primer ~ 8ml / m¹, corresponds to Width 50 mm 1000 ml bottle ~125 m¹ / 1000 ml bottle SikaTack®-Panel Fixing Tape, $1 \text{ m}^{1} / \text{ m}^{1}$ Roll 33 m **Substrate Quality** Clean and dry, homogeneous, even, free from oils and grease, dust and loose or friable particles. Paint, laitance and other poorly adhering particles must be removed. Standard construction rules must be observed. **Applications** Conditions / Limitations **Substrate Temperature** For 5 hours after mounting, the temperature should not fall below the minimum temperature of +5°C. **Ambient Temperature** +5°C min. / +35°C max. **Material Temperature** The temperature of the building components to be bonded (cladding panels, sub structure etc.) must be at least 3°C higher than the dew point temperature of the air in order to avoid the formation of condensation on the surfaces. Substrate Humidity Dry, wood moisture content < 14%. **Relative Air Humidity** Max. 75% **Application** Instructions Application Method / Aluminium substructures: **Tools** Clean with a fine abrasive pad e.g. Scotch Brite very fine. Clean the surface with a clean, greaseand fluff free cellulose cloth or cleaning paper soaked in Sika® Cleaner-205 by wiping the surface in one direction only (dirty cloths must be replaced). Allow a flash off time of at least 10 minutes. Shake the SikaTack®-Panel Primer thoroughly (the movement of the steel

balls in the container must be clearly

with a brush or felt pad.

Allow a flash off time of at least 30 minutes (maximum 8 hours).

Apply one thin coat of SikaTack[®]-Panel Primer uniformly all over the surface

audible).

Tim	ber substructures:		
	Remove dust.		
	Shake SikaTack®-Panel Primer thoroughly (the movement of the steel balls in the container must be clearly audible).		
	Apply one thin coat of SikaTack®-Panel Primer uniformly over the whole surface with a brush or felt pad.		
	Allow a flash off time of at least 30 minutes (maximum 8 hours).		
Do nor Sik	ution not use cloudy or whitish Sika [®] Cleaner-205 or a n-homogeneous Primer. Fully cured Primer can c a [®] Cleaner-205 leaves a cloudy film. Only the su ated. Under all circumstances minimum flash off	only be removed mechanical irface to be bonded must be	


or cleaners must be complied to. Splashes on visible surfaces must be removed immediately with a clean cloth or cleaning paper.

Pre treatment of cladding panels:

- The surface to be bonded must be clean, dry and free from grease. After the application of the primer, surfaces must be protected against dirt, dust, grease etc..
- Manual cleaning with an abrasive pad (e.g. Scotch Brite very fine) or mechanical grinding of the surfaces to be bonded with a very fine grinder, (grain 80).
- Clean the surface to be bonded with a clean, grease free and fluff free cloth or cleaning paper soaked in Sika® Cleaner-205 by wiping in one direction only (dirty cloths must be replaced).
- Allow a flash off time of 10 minutes.
- Ceramics and cementitious panels must always be cleaned by grinding. Vacuum clean all surfaces after grinding.

Note: Ceramic and cementitious panels do not clean with Sika® Cleaner-205.

- Shake SikaTack®-Panel Primer thoroughly (the movement of the steel balls in the container must be clearly audible)
- Apply one thin coat of SikaTack®-Panel Primer uniformly over the whole surface with a brush or felt pad.
- Allow a flash off time of at least 30 minutes (max. 8 hours).



Always comply with the panel manufacturers instructions with regard to storage of the panels. Prior to bonding the panels avoid exposure to heat or direct sunlight.

Important Note:

These are general pre-treatment instructions. For the many different façade cladding panels available on the market, different or additional pre-treatments may be required. Thus always refer to the panel manufacturers instructions.

	- Apply SikaTack®-Panel Fixing Tape over the whole length of the vertical sections and parallel to the edges. Do not pull off the protective foil at this time.						
	Bonding-Adhesive Application:						
	 Apply SikaTack®-Panel Adhesive in a triangular bead by using the triangular nozzle supplied (width 8 mm, height 10 mm) with at least 5 mm gap to the fixing tape and to the side of the batten. Application should be with Sika® hand or compressed air guns. 						
	Panel placing:						
	- Remove the protective foil on the SikaTack®-Panel Fixing Tape. Place the cladding panel in the required position on the adhesive bead without the panel touching the fixing tape. To simplify mounting, the panels should be carefully designed. Position the panels precisely and press them firmly until they contact the SikaTack Panel fixing tape.						
	Important Note: Placing of the panels must be completed within 10 minutes after application of the adhesive to the battens of the supporting substructure.						
Cleaning of Tools	Clean all tools and application equipment with Sika® Colma-Cleaner immediately						

Bonding-Tape Application:

Notes on Application /	This product may only be used by professional and experienced applicator.							
Limitations	All panel bonding / fixing works should only be carried out by suitably qualified, trained and experienced contractors and their operatives. Always ensure proper treatment of panels and apply SikaTack® Panel on trial area first.							
	Bonding work can be carried out in the workshop or at site. The work must be protected from weather and dust. During application, the air temperature must not fall below +5°C or exceed +35°C. The relative air humidity must not be more than 75%. For 5 hours after mounting, the temperature should of fall below the minimum temperature of +5°C. The temperature of the building part to be bonded (facade panels, sub construction) must be at least 3°C higher than the dew point temperature of the air in order to avoided the formation of condensation on the surface.							
	For indoor application the SikaTack [®] Panel Primer may only be applied in good ventilated rooms. During application smoking is prohibited. Do not apply SikaTack [®] Panel Primer close to ignition sources.							
	Consultation of the local fire insurance might be necessary in some cases.							
	Daily Records (see Page 10) must be filled in completely and send within 7 days to the supplying company. This is the only way to claim any warranty. Warranties only to general term and conditions.							
Notes	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.							
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.							
Health and Safety Information								
Protective Measures	To avoid allergic reactions, we recommend the use of protective gloves. Change soiled work clothes and wash hands before breaks and after finishing work. During application in closed rooms, pits and shafts, etc., sufficient ventilation must be provided. Uncured material is water pollutant and must not be discharged into drains, waterways or the ground.							
	Local regulations as well as health and safety advice on packaging labels must be observed.							
Ecology	For the most current information please refer to the Material Safety Data Sheet available from Sika Ltd, China upon request.							
Transportation Class	For the most current information please refer to the Material Safety Data Sheet available from Sika Ltd, China upon request.							
Important Notes	Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities. Detailed health and safety information as well as detailed precautionary measure e.g. physical, toxicological and ecological data can be obtained from the material safety data sheet.							
Toxicity	For the most current information please refer to the Material Safety Data Sheet available from Sika Ltd, China upon request.							
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.							

General	Contractor Project										
	Company:					Project name:					
	Address:	Address:				Address:					
	Names of operatives: Start date:			art date:	: End date:						
	Training ob					obtained: Y / N When:					
	Sunny:	0			Overcast	Overcast:		Rainy:		0	
Weather Conditions	Air temp.:	Min. °F / C (morning			(morning)	g) Min. °F / C (midday) Indicate °C or °F					
Troution Conditions	Air humidity:	%			%					Relative hum	idity
Construction Details	Panel										
	Material of pa	nel:			Adhesio	n tes	ted by:				
	Max. length:							mm / i	n	Indicate mm	or in
	Max. width:						mm / i	n	Indicate mm	or in	
	Thickness:					mm / in Indicate mm or i					or in
	Max. weight:					kg / lb Indicate kg or lb					r lb
		and under-const other poorly adh						grease ar	nd du	ıst. Paint,	
Cladding panel treatment	Pre-treatment of the cladding panels										
	Grinding (i. e. Scotch Brite very fine):						Flash off time				
	Sika®Cleaner-205:			/ N		Time: m		min	nin.:		
	SikaTack [®] -Pa	kaTack [®] -Panel Primer: Y / N				Time min.:				.:	
	Wood*:	Dry on surface	()	Dust free	0	None impreg	ınation	0	Planed	0
	Aluminium:	Dry	()	Dust free	0	Free of great	se	0	Smooth	0
	*Note: Moist	ure content of wo	> boc	14%	6						
Substructure treatment	Pre-treatmen	t of the substruc	ture								
	Grinding (i. e. Scotch Brite very fine):						Flash off time				
	Sika®Cleaner-205: Y / N						Time: m		min	in.:	
	SikaTack®-Panel Primer: Y / N				Time: min.:			.:			
Bonding the panel to the substructure	SikaTack®-Panel Fixing Tape:			Ye	es	O Applied on full length			Y/N		
iubsti ucture	SikaTack®-Panel Adhesive:			Ca	artridge	0	O Unipac O				
	Batch nr:					Best before:					
	Place and da	te:									



Sika (Guangzhou) Trading Comapny Ltd,
Room 2, Level II,
No. 96 JunDa Road
Eastern Section
GET, Guangzhou
China
Post Code 510530
Tel: (86) 20 8226 6066
Fax: (86) 20 3206 6428
Email: marketing@cn.sika.com
Web-site: www.sika.cn