

DESCRIPTION:

RC-2410 4:1 primer (Grey/Black/White) is multi-purpose double pack primer surfacer, with strong filling power and fine adhesion between coats, has excellent flexibility and impact resistance which can increase gloss and build of topcoat.

AUXILIARY PRODUCTS:

RC-2410/2410B/2410W	4:1	Primer
RC-2641		Fast Activator
<64°F		
RC-2643		Medium Activator
64-86°F		
RC-2644		Slow
Activator	>86°F	

SUBSTRATES:


Dried and sanded old paint films, primers and putty.

SURFACE PREPARATION:




Remove wax, silicon and other contaminations with degreaser.

MIXING RATIO:



T(°F)	Product	Volume	Weight
<64°F	RC-2410	100	150
	RC-2641	25	25
	R-1	20-30	20-30
64-86°F	RC-2410	100	150
	RC-2643	25	25
	R-2	20-30	20-30
>86°F	RC-2410	100	150
	RC-2644	25	25
	R-3	20-30	20-30

POT-LIFE:



@ 74°F:
30mins with RC-2641
1h with RC-2643, RC-2644

APPLICATION VISCOSITY:

20-24s (74°F, DIN -4 Cups)

APPLICATION:



Spray gun set up:

RP: 1.6mm

26-29 psi

Please refer to gun manufacturer for proper spray pressure recommendations.



Coats & Thickness:

2-3 Coats, 40-60um,
5-10 mins between coats@74°F

DRYING

TIME:



T(°F)	Time
59°F	5hrs
74°F	3hrs
140°F	30mins

SANDING:

Dry sanding: 400#-600#

Wet sanding: 800#-1000#

RE-APPLICATION

After drying and sanding, it can be sprayed with various topcoats.

NOTE:

- Shelf-life: 2 years in original sealed can at cool and dry place at 68°F.

PHYSICAL DATA:

Regulatory VOC (RTS): 4.6 lb/gal

FOR PROFESSIONAL USE ONLY

Read MSDS Before Use

NOTE: The information in this data sheet is based on our knowledge and the current laws. It is always the responsibility of the user to fulfill the requirements of local rules and legislation. The uncertain factors may affect the application of products, such as the condition of

substrate. We do not accept any liability on loss, damage and performance of products unless we issue a special agreement. Always read the latest Material Data Sheet and the Technical Data sheet before applying the products.
