

## MAXLV-3520 1K Binder

For in the MAXLV-1K basecoat system. Uses to speed up air drying time, enhance the orientation of silver & pearl particles, and improve the application properties.

For use with: MAXLV 1K Basecoat toners.

	Lload to anough up air drying time, anhance the orientation of ailyar 9		
Characteristics	MANUA 0500	Used to speed up air drying time, enhance the orientation of silver & pearl particles, and improve the application properties of the	
	MAXLV-3520	basecoat.	
		Used to lighten the side tone of the metallic basecoat color and	
	MAXLV-60	create a darker face with the added appearance of larger metallic sparkle.	
Mixing ratio	Mixing ratio:		
	1. Addition of MAXLV-3520 to MAXLV 1K metallic basecoat is 15-40% of total toner		
	volume.		
	2. For MAXLV 1K silver, white, or other lightly colored metallic basecoat, it is		
	recommended that no less than 25% MAXLV-3520 is used. If silver basecoat is used		
	individually, add 40% MAXLV-3520.		
	3. In tri-coat pearl/candy colors, add up to 50-70% of MAXLV-3520 into the pearl		
	colors.		
	4. For basecoat colors with poor coverage, such as red pearl colors, the addition of		
	MAXLV-3520 should be less than 15% so as not to affect the coverage of the		
	basecoat.		
	5. 20% or less of MAXLV-60 can be used to lighten the side tone of metallic colors,		
	and create a darker face with appearance of increased metallic sparkle. Adding too		
	much of MAXLV-60 will affect the adhesion between the basecoat and clear coat.		
Shelf Life	2 years in original sealed can at cool and dry place at 41-95°F		
VOC	3.5 lb/gal(mixed)		