

DESCRIPTION:

- Multi-purpose double pack primer surfacer, with strong filling power and fine adhesion between coats, has excellent flexibility and impact resistance which can increase gloss and build of topcoat.
- High isolating ability and high build property.
- Excellent adhesion to putties, fillers and properly sanded hardened paints.
- Easy to apply, excellent leveling and sanding property.
- Give proper basis to get good finish without absorbing the paint's gloss.

AUXILIARY PRODUCTS:

EC-5410W	4:1 Primer	
EC-5641	Primer Fast Activator	<77°F
EC-5643	Primer Standard Activator	>77°F

SUBSTRATES:


Dried and sanded old paint films, primers and putty.

SURFACE PREPARATION:



Remove wax, silicon and other contaminations with degreaser.

MIXING RATIO:



T (°F)	Product	Volume	Weight
< 77°F	EC-5410	100	150
	EC-5641	25	25
	E-1	20-30	20-30
>77°F	EC-5410	100	150
	EC-5643	25	25
	E-2	20-30	20-30

POT-LIFE:



@ 74°F:
30mins with EC-5641
1h with EC-5643

APPLICATION VISCOSITY:

20-24s (74°F, DIN -4 Cups)


APPLICATION:



Spray gun set up:

RP: 1.6mm 26-29 psi

Please refer to gun manufacturer for proper spray pressure recommendations.



Coats & Thickness:

2-3 Coats, 40-60um,
5-10 mins between coats@74°F

DRYING TIME:



T(°F)	Time
59°F	5hrs
74°F	3hrs
140°F	30mins

SANDING:

Dry sanding: 400#-600#

Wet sanding: 800#-1000#

RE-APPLICATION

After drying and sanding, it can be sprayed with various topcoats.

NOTE:

- Shelf-life: 2 years in original sealed can at cool and dry place at 68°F.

PHYSICAL DATA:

Regulatory VOC (RTS): 3.17 lbs/gal

FOR PROFESSIONAL USE ONLY

Read MSDS Before Use

NOTE: The information in this data sheet is based on our knowledge and the current laws. It is always the responsibility of the user to fulfill the requirements of local rules and legislation. The uncertain factors may affect the application of products, such as the condition of substrate. We do not accept any liability on loss, damage and performance of products unless we issue a special agreement. Always read the latest Material Data Sheet and the Technical Data sheet before applying the products.