

Series: Travertini Porcelain Tile


TRAVERTINI

Stocked

COLORS




Bianco



IRG12M112P
2" x 2" Bianco
Mosaic




Grigio



IRG12M113P
2" x 2" Grigio
Mosaic



Argento



IRG12M114P
2" x 2" Argento
Mosaic

Special
Order

Stocked

SIZES	24"x48" matte	12"x24" matte
Bianco	IRG2448112	IRG1224112
Grigio	IRG2448113	IRG1224113
Argento	IRG2448114	IRG1224114

TRIMS

Stocked



BULLNOSE
4"x24" Matte

Bianco	IRG424BT112
Grigio	IRG424BT113
Argento	IRG424BT114

MOSAICS

Stocked



2"x2" MOSAIC
12"x12" Matte

Special
Order



BRICK 03 MOSAIC
12"x12" Matte

Bianco	IRG12M112P	IRG12MB112
Grigio	IRG12M113P	IRG12MB113
Argento	IRG12M114P	IRG12MB114

PACKAGING INFORMATION

SIZE	PCS/ BOX	SF/ BOX	THICKNESS (mm)
24" x 48"	2	15.50	8.0
12" x 24"	8	15.751	8.0
MOSAICS on 12"x12" Sheet			
MOSAIC 2"x2"	5	4.896	8.0
BRICK 03 2"x6"	5	4.896	8.0
BULLNOSE 4"x24"	16	15.585	8.0



* All sizes are nominal
* Printed color reproductions may vary from actual tile color

Series: Travertini Porcelain Tile

3. TECHNICAL DATA

Physical Properties	ASTM Test	Industry Standards	Iris US Results
Water Absorption	C373	Impervious <0.5%	≤ 0.1%
Thickness Dimension	C499	Range ±0.04in Max.	≤ ±0.04 in
Facial Dimension	C499	±0.25%	≤ ±0.25%
Warpage Average	C485	± 0.40% on any edge	≤ ± 0.40%
Warpage Average	C485	± 0.40% on diagonal	≤ ± 0.40%
Wedging Average	C502	± 0.25%	≤ ± 0.25%
Bond Strength	C482	≥ 50 psi	≥ 200 psi
Breaking Strength	C648	≥ 250 lbf	≥ 400 lbf
Hardness (Mohs)	Scratch Test (No regulated)	Range 0 - 10	≥ 7
Visible Abrasion Resistance for Glaze Tile	C1027	No requirement Range 0 - 5	Class 4
Frost Resistance (Freeze/Thaw)	C1026	No sample must show alterations to surface	No evidence of damage
Chemical Resistance	C650	No Requirement Range E - A	Class A
Stain Resistance	C1378	No Requirement Range E - A	Class A*
Coefficient of Friction (Dynamic)	DCOF Acutest sm (wet)	≥ 0.42	≥ 0.50*
Aesthetic Classification	Visual Evaluation Shade & Texture	No Requirement Range V0 – V4	V2

* All values given are for matte or honed material. No values are given for polished material. Iris U.S. does not recommend polished surfaces in area subject to exposure from grease, oil or water.

For level interior spaces to be walked upon when wet (see ANSI A137.1 section 6.2.2.1.10 – Section 9.6 for test procedure).



INSTALLATION

All installation work using tiles will conform to the standards set forth in the latest version of ANSI A108/118 and/or the TCNA Handbook for Ceramic Tile installations.

Installation or setting materials:

Movement joints shall be provided throughout the tile and work will conform to ANSI Specification A108.01-3.7; A108.02 – 4.4. and TCNA Details EJ171.

Setting materials used will conform to the ANSI 118.4 standard or greater and be recommended by the selected manufacturer for the installation & setting materials for ceramic or porcelain tile based on the application requirements.

WARRANTY

It is guaranteed that its products will be free of manufacturing defects and they will meet or exceed the performance specifications set forth in ANSI 137.1.

MAINTENANCE

Care and Maintenance Recommendations Guide

Please contact your sales representative

TECHNICAL SERVICES

Technical Assistance

Guide Specifications, literature, MSDS, tile samples, details and installation procedures are all available for your use or libraries.

Series: Travertini Porcelain Tile



TRAVERTINI

