



**35 Prospect Place
Deer Park, NY 11729
631-254-4381**

CORK & NITRILE

Revised 6/23

BINDER	NITRILE
DENSITY, LBS/FT ³	40
TENSILE, PSI	250
COMPRESSION @ 400 psi	25 - 35
RECOVERY	75
FLEX	3
HARDNESS	65 + -10 DURO SHORE A
VOLUME CHANGE %	
ASTM OIL #1	0 to +10
ASTM OIL #3	+5 to +15
FUEL A	0 to +10
ASTM #	P-2245A
AMS-C-6183 B	CLASS 1, GRADE B
F-104 CALL OUT	F-226000

RECOMMENDED USES: MEDIUM COMPRESSIBLE MATERIAL WITH GOOD TENSILE STRENGTH AND EXCELLENT RESISTANCE TO SOLVENTS AND TRANSFORMER OILS.