



**35 Prospect Place
Deer Park, NY 11729
631-254-4381**

CORK & NEOPRENE

Revised 6/23

BINDER	NEOPRENE
DENSITY, LBS/FT3	42
TENSILE, PSI	250
COMP. @ 400 psi	25 - 35
RECOVERY	80
FLEX	3
HARDNESS	65 + - 10 DURO SHORE A
VOLUME CHANGE %	
ASTM OIL #1	0 to +5
ASTM OIL #2	+10 to +30
FUEL A	0 to +10
ASTM #	P-2255A
MIL C 6183 B	CLASS II, GRADE B
F-104 CALL OUT	F-229000