



**35 Prospect Place
Deer Park, NY 11729
631-254-4381**

Peroxide Cure EPDM

Revised 6/23

Material
Color
Temperature

EPDM
Black
-55° F to +300° F

Durometer Hardness Shore A +/- 5	Tensile	Elongation	Specifications
40	1200	500	MICA 410, ASTM D 2000
50	1500	450	MICA 510, ASTM D 2000
60	1700	400	MICA 610, ASTM D 2000
70	1700	200	MICA 710, ASTM D 2000
80	1800	150	MICA 810, ASTM D 2000