



**35 Prospect Place
Deer Park, NY 11729
631-254-4381**

EPDM RUBBER

Revised 06/23

MATERIAL	ETHYLENE PROPYLENE DIENE METHYLENE TERPOLYMER
COLOR	BLACK
HARDNESS	60 SHORE A +/-5
TENSILE	750 PSI
ELONGATION	300%
TEMPERATURE	-40°F to +210°F
FINISH	SMOOTH
WIDTHS AVAILABLE	36" - 48"

RECOMMENDED USES - ALL OUTDOOR APPLICATIONS DUE TO ITS WEATHER RESISTANCE TO SUNLIGHT, OZONE & OXIDANTS. ADDITIONALLY, IT IS RESISTANT TO ANIMAL & VEGETABLE OILS, WATER, STEAM, OXYGENATED SOLVENTS(ACETONES), METHYL ETHYL KETONE(MEX) AND OTHER KETONES.

RESULTS – ABOVE BASED ON 60+-5 DURO 40, 50, 70 AND 80+-5 DURO'S AVAILABLE

NOTE: This is a general guide and should not be the sole means of selecting or rejecting this material. Results listed are typical and not minimums. Requirements should not be based on typical values.