

Revised 6/23

35 Prospect Place Deer Park, NY 11729 631-254-4381

COMMERCIAL GRADE FLUOROELASTOMER SHEET

Is a quality commercial grade fluoroelastomer sheet designed for applications, which require a 75 durometer material with good chemical and heat resistance.

<u>Property</u>	Typical Value	Test Method
Service Temperature:	350°F Continuous 400°F Intermittent	
Hardness:	75 Shore A	ASTM D 2240
Specific Gravity:	1.88	ASTM 792
Tensile Strength:	1000psi	ASTM D 412
Elongation:	350%	ASTM D 412
Compression Set: (22h at 350°F)	37%	ASTM D 395B

ASTM D 2000M2HK707B37EF31F15

Performs well in hydrocarbons
Also in certain acids

Call us for your special application questions.

THIS INFORMATION IS BASED ON DATA THAT WE BELIEVE TO BE RELIABLE. IT IS INTENDED FOR USE BY PERSONS HAVING TECHNICAL SKILLS OF THEIR OWN DISCRETION AND RISK. SINCE CONDITIONS OF PRODUCT USE ARE OUTSIDE OUR CONTROL, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. NOTHING HEREIN IS TO BE TAKEN AS A LICENSE TO OPERATE UNDER OR A RECOMMENDATION TO INFRINGE ANY PATENTS.

Your One Reliable Fluid Sealing Source