

Fortis CRCF-PC 3D Printing Filament is a new PC-CF type filament with a double-layer structure. Called coated Carbon fiber filament, C-CF PC range filament has increased the Carbon/Glass fiber content of PC-GF to 15-25%. Not only the content is increased, but also fiber length increase to 0.1-0.5mm, because of the Aspect ratio increasing, model be printed with more strength.



Physical Properties	Typical Value
---------------------	---------------

Material Density	1.18-1.22g/cm ³
Carbon fiber surface content	15-20%
Fiber length	0.1-3mm

Physical Parameters	Typical Value
---------------------	---------------

Heat deflection temperature	80-92°C
Tensile Strength (3D Printing)	65MPa
Elongation at Break	≤12%

Printing 100% Infilling Parameter	Typical Value
-----------------------------------	---------------

Printing temperature	260-280°C
Platform temperature	≥90°C
Printing speed	60-120mm/s
Printing speed (M.V.S)	8-12mm ³ /s
Enclosed chassis	Y
Cooling Fan	0%

Size	N.W	G.W	Diameters	Packing Characteristic
XM	500g	700g	1.75mm / 2.85mm / 3.00mm	SmartBag, Security Seal
L	1000g	1200g	1.75mm / 2.85mm / 3.00mm	SmartBag, Security Seal

