

REPORT NUMBER:
102166079SAT-001A ORIGINAL ISSUE
DATE: June 28, 2015 REVISED DATE:

EVALUATION CENTER Intertek
Testing Services NA Inc. 16015
Shady Falls Road Elmendorf,
TX 78112

**RENDERED
TO**

Valspar Corporation
4602 Elevation Way
Fort Myers, FL
33905

Report of Testing "Valspar WeatherXL" for compliance with the applicable

requirements of the following criteria: ASTM E84-15 TEST FOR SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS (UL 723, UBC 8-1, NFPA 255)

Page 1 of 9

Project No. 102166079SAT-001A June 28, 2015 Valspar Corporation Page 2 of 9

ABSTRACT

Specimen I. D. "Valspar WeatherXL"

Test Standard: ASTM E84-15 TEST FOR SURFACE BURNING
CHARACTERISTICS OF BUILDING MATERIALS
(UL 723, UBC 8-1, NFPA 255)

Test Date: June 23, 2015

Client: Valspar Corporation

Test

Results:

**FLAME SPREAD INDEX 0 SMOKE
DEVELOPED INDEX 5**

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of the report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

Joseph Martinez

Technician III

Reviewed and
approved:

Servando Romo
Project Engineer

Project No. 102166079SAT-001A June 28, 2015 Valspar Corporation Page 3 of 9

I. INTRODUCTION

This report describes the results of the ASTM E84-15 TEST FOR SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS a method for determining the comparative surface burning behavior of building materials. This test is applicable to exposed surfaces, such as ceilings or walls, provided that the material or assembly of materials, by its own structural quality or the manner in which it is tested and intended for use, is capable of supporting itself in position or being supported during the test period.

The purpose of the method is to determine the relative burning behavior of the material by observing the flame spread along the specimen. Flame spread and smoke density developed are reported, however, there is not necessarily a relationship between these two measurements.

“The use of supporting materials on the underside of the test specimen may lower the flame spread index from that which might be obtained if the specimen could be tested without such support... This method may not be appropriate for obtaining comparative surface burning behavior of some cellular plastic materials... Testing of materials that melt, drip, or delaminate to such a degree that the continuity of the flame front is destroyed, results in low flame spread indices that do not relate directly to indices obtained by testing materials that remain in place.”

This test method is also published under the following designations:

NFPA 255

This standard should be used to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use.

Project No. 102166079SAT-001A June 28, 2015 Valspar Corporation Page 4 of 9

II. PURPOSE

The ASTM E84 (25 foot tunnel) test method is intended to compare the surface flame spread and smoke developed measurements to those obtained from tests of mineral fiber cement board and select grade red oak flooring. The test specimen surface (18 inches wide and 24 feet long) is exposed to a flaming fire exposure during the 10 minute test duration, while flame spread over its surface and density of the resulting smoke are measured and recorded. Test results are presented as the computed comparisons to the standard calibration materials.

The furnace is considered under calibration when a 10 minute test of red oak decking will pass flame out the end of the tunnel in five minutes, 30 seconds, plus or minus 15 seconds. The fiber cement board which complies with Annex A3 of the ASTM E 84 standard forms the zero point for both flame spread and smoke developed indexes, while the red oak flooring smoke developed index is set as 100.

III. TEST PROCEDURE

The tests were conducted in accordance with the procedures outlined in the ASTM E84. The specimens are placed directly on the tunnel ledges. As required by the standard, one or more layers of 0.25 inch thick reinforced concrete board are placed on top of the test sample between the sample and the tunnel lid. After the test, the samples are removed from the tunnel, examined and disposed of.

IV. REVISION SUMMARY

DATE SUMMARY June 28, 2015 Original

Project No. 102166079SAT-001A June 28, 2015 Valspar Corporation Page 5 of 9

V. DESCRIPTION OF TEST SPECIMENS

Date Received: 6/18/2015 Date placed in
the conditioning room: 6/18/2015

Conditioning (73°F & 50% R.H.): 5 days

Specimen Width (in): 24 Specimen

Length (ft): 24 Specimen Thickness

(in): 0.02 Total Specimen Weight

(lbs): 30

Specimen Description: The specimen was described by the client as “Coil Coated Silicone Polyester”.

The 24 ft. long test specimen consisted of three 8 ft. long sections of coated sheet metal.

The product was received by our personnel in good condition and given an identification number of SAT1506181613-001.

Mounting Method: The specimen was supported by rods. The coated side was exposed towards the flames.

Project No. 102166079SAT-001A June 28, 2015 Valspar Corporation Page 6 of 9

VI. TEST RESULTS & OBSERVATIONS

The test results, computed on the basis of observed flame front advance and electronic smoke density measurements are presented in the following table.

Test Specimen Flame Spread	Smoke Developed Index
“Valspar WeatherXL” 0 5	

The data sheets are included in Appendix A. These sheets are actual print-outs of the computerized data system which monitors the tunnel furnace, and contain all calibration and specimen data needed to calculate the test results.

VII. OBSERVATIONS

During the test, the specimen was observed to behave in the following manner.

Time (min:sec) Observations

0:00 The test burners were turned on. 0:47 Steady ignition was observed. 1:27 The specimen began to sag. 10:00 The test burners were shut off.

After the test, the specimen was observed to be damaged as follows:

Distance

(FEET) Damage Descriptions

0 – 4 The coating was observed to be heavily charred and cracked with pieces of flaked coating on the tunnel floor. 4 – 15 The coating was observed to be lightly discolored. 15 – 24 No visible damage was observed.

APPENDIX A
ASTM E84 DATA
SHEETS

Project No. 102166079SAT-001A June 28, 2015 Valspar Corporation Page 8 of 9
Project No. 102166079SAT-001A June 28, 2015 Valspar Corporation Page 9 of 9