

UnParallel Rubber Physical Properties



NAME	UP RS		UP VD		UP VC		UP RH		UP VS	
	REAL SUPREME		VIRTURAL DEMPING		VIRTURAL COLORS		REAL HONOR		VIRTUAL STEADY	
PHYSICAL DATA	SHORE A (HRDNESS)	65-70	SHORE A (HRDNESS)	45-50	SHORE A (HRDNESS)	58-65	SHORE A (HRDNESS)	76-80	SHORE A (HRDNESS)	67-71
	RESILIENCE (REBOUND)	11%	RESILIENCE (REBOUND)	8%	RESILIENCE (REBOUND)	25%	RESILIENCE (REBOUND)	13%	RESILIENCE (REBOUND)	12%
	DIN ABRASION	285	DIN ABRASION	N/A	DIN ABRASION	190	DIN ABRASION	290	DIN ABRASION	260
TOLERANCE	+/- 5%		+/- 5%		+/- 5%		+/- 5%		+/- 5%	
COMPOUND MIXING	CA, USA		CA, USA		CA, USA		CA, USA		CA, USA	
APPLICATION	CALENDER ROLL	USA	CALENDER ROLL	USA			CALENDER/SHEET	USA		
	PRESSED OUTSOLE	ASIA	PRESSED OUTSOLE	ASIA	PRESSED OUTSOLE	ASIA			PRESSED	ASIA