



# ADVANCE INSPECTION & TESTING LAB



B/119, Mayapuri Industrial Area, Phase 1, New Delhi-110064  
Web.: [www.advancetestinglab.com](http://www.advancetestinglab.com), Email : [advancetestinglab@gmail.com](mailto:advancetestinglab@gmail.com)  
Tel: 91-9810-55-8484, 91-9891-35-3939

## TEST REPORT

FF:7.8.1.1

Issued To: M/s Roop Petrochemical  
HSIIDC Industrial Area Sector-37  
Gurgaon,HR

W.O No: AITL/2281/02  
Report No: 23020402  
Date of Issue: 20-07-2023  
Date of Receipt: 04-07-2023  
Party Ref. No: PV & Email Dated 04-07-2023  
Order Confirmation Date: 04-07-2023

## SAMPLE PARTICULARS

PAGE 1 OF 1

1. **Sampling Method:** Sampling done by the laboratory
2. **Sample Deposited:** By party
3. **Sample Description:** Two sample described by party as hydraulic oil was received for following test only.

## SPECTRO TEST RESULTS

	TYPE OF METHOD	AF-2A	AF-2C
Colour	ASTM D-1500	L0.5	L0.5
Density 15 °C g/cm <sup>3</sup>	ASTM D-4052	0.7636	0.7652
Viscosity, cST @ 40 °C	ASTM D-445	1.328	1.400
Flash Point, (PM) °C	ASTM D-93	53	57
Total Acid No. (mgKOH/g)	ASTM D-974	0.01>	0.01>
Copper Corrosion (Room Temp. x 24 Hrs)		1(1A)	1(1A)

DR. VIRENDER TAANDON

Authorised Signatory

Civil / Mechanical / Chemical / NDT TESTING

1. The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. 2. Total liability of our lab is limited to the invoiced amount. 3. Samples will be destroyed after 15 days from the date of test certificate unless specified otherwise. 4. The Report shall not be reproduced except in full without written approval of Laboratory. 5. Report refers to the sample submitted to us and not drawn by Advance Inspection & Testing Lab unless mentioned otherwise. 6. In case of any dispute, the Jurisdiction shall be New Delhi Courts.