

COLPLY ADHESIVE TROWEL GRADE

TECHNICAL DATA SHEET 200106SCANE

(supersedes 190805SCANE)



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFS

DESCRIPTION

COLPLY ADHESIVE TROWEL GRADE is a SBS modified bitumen based adhesive. COLPLY ADHESIVE TROWEL GRADE is used to adhere SBS bituminous membranes on flashings and slope surfaces > 3 % (3/8 in per ft).

On low slopes (< 3 % [3/8 in per ft]), use COLPLY ADHESIVE BRUSH GRADE adhesive.

SURFACE PREPARATION

All surfaces should be dry, clean and free from oil, grease, dirt and loose materials.

APPLICATION

COLPLY ADHESIVE TROWEL GRADE adhesive is applied using a 4.8 mm (3/16 in) or a 6.0 mm (1/4 in) notched squeegee in order to apply a uniform coat as per the recommended coverage rate.

The minimum application temperature is 0 °C (32 °F). Curing time was determined under ideal application conditions: 25 °C (77 °F) and 50% relative humidity. Curing time will be longer at lower temperatures.

FOR COMPLETE INFORMATION ON PRODUCT APPLICATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	COLPLY ADHESIVE TROWEL GRADE
Physical state	Liquid
Colour	Black
Container	310 ml (10.4 oz) 10L (2.2 US Gallon) 19 L (5.0 US Gallon)
Coverage rate per container of :	
310 ml	0.4 m ² (4.3 pi ²)*
10 L	12 m ² (129 pi ²)*
19 L	23 m ² (250 pi ²)*

*Coverage rate may vary depending on the application technique and the substrate condition.
(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS_COLPLY_ADHESIVE_TROWEL_GRADE.indd

COLPLY ADHESIVE TROWEL GRADE

TECHNICAL DATA SHEET 200106SCANE

(supersedes 190805SCANE)



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFS

PROPERTIES

COLPLY ADHESIVE TROWEL GRADE adhesive meets and exceeds the recommendations of ASTM D7379 standard.

Properties	Standards	COLPLY ADHESIVE BRUSH GRADE
Density	-	0.90 kg/L (7.5 lb/US gal)
Solids by weight	-	75 %
Lap adhesion	ASTM D3019	3.5 kN/m
Fully cured	-	30 days, depending on temperature and quantity applied

Note: Coverage rate is approximate and may vary due to the application technique and surface roughness.
(All values are nominal)

CLEANING

Tools and uncured adhesive can be cleaned with solvents, such as mineral spirits, Varsol, Xylene, etc.

STORAGE AND HANDLING

Storage : Up to 12 months, stored in original sealed containers. COLPLY ADHESIVE TROWEL GRADE must be stored between 5 to 40 °C (41 to 104 °F). Store in a ventilated place, away from heat and direct sunlight.

For more information, refer to instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS_COLPLY_ADHESIVE_TROWEL_GRADE.indd