1. Identification of the substance/mixture and of the company/undertaking

Manufacturer: E. I. du Pont de Nemours and Company. DuPont Performance Coatings Wilmington, DE 19898

Telephone:	Product information:	(800) 441-7515
	Medical emergency:	(800) 441-3637
	Transportation emergency:	(800) 424-9300 (CHEMTREC)

Product: Imron (R) 6000 Polyurethane Enamel

DOT Shipping Name: See DOT Addendum.

Hazardous Materials Information: See Section 10.

Copyright 2011 E. I. du Pont de Nemours and Company. All rights reserved. Copies may be made only for those using DuPont products.

2. Composition/information on ingredients

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
	96591-17-2	None	A None, O None
1,2,4-trimethyl benzene	95-63-6	7.0@44.4 °C	A 25.0 ppm, O 25.0 ppm
1,6-hexamethylene diisocyanate	822-06-0	0.0@25.0°C	A 5.0 ppb, O None
2,4-pentanedione	123-54-6	9.0	A 25.0 ppm Skin, D 5.0 ppm 8 & 12 hour TWA, O None
2-ethylhexyl acetate	103-09-3	0.5	A None, O None
2-methyl butyl acetate	624-41-9	None	A 100.0 ppm 15 min STEL, A 50.0 ppm, O None
4-chlorobenzotrifluoride	98-56-6	7.6@25.0 °C	D 20.0 ppm 8 & 12 hour TWA, A None, O None
Acetone	67-64-1	247.0@68.0°F	A 750.0 ppm 15 min STEL, A 500.0 ppm, O 1000.0 ppm,
	07 01 1	217.00000.0 1	D 500.0 ppm 8 & 12 hour TWA
Acrylic polymer-A	NotAvail	None	A None, O None
Acrylic polymer-B	104032-39-5	None	A None, O None
Acrylic polymer-C	170475-04-4	None	A None, O None
Acrylic polymer-D	206987-67-9	None	A None, O None
Acrylic polymer-E	25067-83-8	None	A None, O None
Acrylic polymer-F	42767-92-0	None	A None, O None
Acrylic polymer-G	69215-54-9	None	A None, O None
Acrylic polymer-G	NotAvail	None	A None, O None
Aliphatic polyisocyanate resin	28182-81-2	<0.0	S 0.5 mg/m3, A None, O None
Aluminum	7429-90-5	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust,
Aluminum	7429-90-5	None	D 0.5 mg/m3 8 & 12 hour TWA, A None
	01045 51 0	Mana	0
Aluminum hydroxide	21645-51-2	None	A 1.0 mg/m3, O None
Amorphous silica-A	7631-86-9	None	A 3.0 mg/m3 Respirable Dust, O 20.0 mppcf, D 3.0
	00707 00 0	0.0	mg/m3, D 6.0 mg/m3
Amorphous silica-B	92797-60-9	<0.0	A 2.0 mg/m3 Respirable Dust, O 1.0 mg/m3 15 min
A 1 11 11 1 1 1 1	110000 00 0		STEL, D 1.0 mg/m3
Amorphous silica - precipitated	112926-00-8	None	O 15.0 mg/kg Total Dust, O 5.0 mg/m3 TWA Respirable
	0.17.10.05.0	10 0005 0.00	Dust, D 3.0 mg/m3 Respirable Dust, A None
Aromatic hydrocarbon	64742-95-6	10.0@25.0°C	D 50.0 ppm, A None, O None
Azo yellow pigment	31837-42-0	None	A 10.0 mg/m3, O 5.0 mg/m3 Respirable Dust, O 15.0 mg/m3
Barium sulfate	7727-43-7	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust,
			D 10.0 mg/m3 Total Dust, D 5.0 mg/m3 8 & 12 hour TWA
			Respirable Dust, A None
Butanedioic acid, dimethyl ester	106-65-0	None	D 10.0 mg/m3, A None, O None
Butyl acetate	123-86-4	10.0	A 200.0 ppm 15 min STEL, A 150.0 ppm, O 150.0 ppm
C.i. pigment blue 60	81-77-6	None	A None, O None
C.i. pigment red 254	84632-65-5	None	A None, O None
C.i. pigment yellow 138	30125-47-4	None	A None, O None
Carbazole violet pigment	6358-30-1	None	A None, O None
Carbon black	1333-86-4	None	A 3.0 mg/m3, O 3.5 mg/m3, D 0.5 mg/m3 8 & 12 hour
			TWA
Cumene	98-82-8	3.7	A 50.0 ppm, O 50.0 ppm Skin
Dibutyl tin dilaurate	77-58-7	<10.0	A 0.2 mg/m3 15 min STEL Sn, A 0.1 mg/m3 Sn, O 0.1
· · ···			mg/m3 Sn
Dimethyl glutarate	1119-40-0	0.2	A None, O None
Ethyl 3-ethoxy propionate	763-69-9	2.0@25.0 °C	A None, O None
Ethyl acetate	141-78-6	93.2@25.0 °C	A 400.0 ppm, O 400.0 ppm
Ethylbenzene	100-41-4	7.0	A 20.0 ppm, O 100.0 ppm, D 25.0 ppm 8 & 12 hour TWA
,		·	

INGREDIENTS	CAS#	VAPOR	EXPOSURE LIMITS
Ethylene glycol monobutyl ether acetate	112-07-2	PRESSURE 0.3	A 20.0 ppm, D 20.0 ppm 8 & 12 hour TWA , O None
Heptane	142-82-5	45.0@66.0 ° F	A 500.0 ppm 15 min STEL, A 400.0 ppm, O 500.0 ppm
Hydrotreated heavy naphtha (petroleum)	64742-48-9	10.0@25.0 °C	A 100.0 ppm, O 500.0 ppm, D 100.0 ppm
Iron oxide	1309-37-1	None	A 5.0 mg/m3 Respirable Dust, O 10.0 mg/m3, D 3.0
Isoindolinone pigment	36888-99-0	None	mg/m3 A None. O None
Isopropyl alcohol	67-63-0	48.0	A None, O None
Light yellow lemon yellow oxide pigment	51274-00-1	None	A None, O None
Methyl acetate	79-20-9	171.3@68.0 ° F	A 250.0 ppm 15 min STEL, A 200.0 ppm, O 200.0 ppm
Methyl amyl ketone	110-43-0	3.4	A 50.0 ppm, O 100.0 ppm
Methyl ethyl ketone	78-93-3	71.2	A 300.0 ppm 15 min STEL, A 200.0 ppm, O 200.0 ppm,
			D 300.0 ppm 15 min TWA, D 200.0 ppm 8 & 12 hour TWA
Methyl isoamyl ketone	110-12-3	5.3	A None, O None
Monoazo pigment	12236-62-3	None	A 10.0 mg/m3 inhalable dust particulate, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust
N-butyl alcohol	71-36-3	5.6@68.0°F	A 20.0 ppm, O 100.0 ppm, D 50.0 ppm 15 min STEL,
N balyr alconor	11000	0.0@00.0 1	D 25.0 ppm 8 & 12 hour TWA
Organoclay	68911-87-5	None	A None, O None
Perylene maroon	5521-31-3	None	A None, O None
Phthalocyanine blue pigment	147-14-8	None	A 10.0 mg/m3 inhalable dust PNOC, A 3.0 mg/m3 res-
			pirable particulate PNOC, O 15.0 mg/m3 Total Dust
Distingtion of the second	1000 50 0	News	PNOR, O 5.0 mg/m3 TWA Respirable Dust PNOR
Phthalocyanine green	1328-53-6	None	A 3.0 mg/m3 TWA Respirable Dust, A 10.0 mg/m3 TWA inhalable dust, O 15.0 mg/m3 TWA Total Dust, O 5.0
			mg/m3 TWA Respirable Dust
Pigment red	NotAvail	None	A None, O None
Pigment red 202	3089-17-6	None	A 3.0 mg/m3 Respirable Dust, A 10.0 mg/m3 inhalable
			dust PNOR, O 5.0 mg/m3 Respirable Dust PNOR, O 15.0
			mg/m3
Poly(oxy-1,2-ethanediyl),.alpha	104810-48-2	None	A None, O None
[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-			
dimethylethyl)-4-hydroxy phenyl Polycaprolactone diol	69089-45-8	<0.0	A None, O None
Polyester resin-A	NotAvail	None	A None, O None
Polyester resin-B	129922-22-1	None	A None, O None
Polyester resin-C	68604-67-1	None	A None, O None
Polyester resin-D	71010-58-7	None	A None, O None
Polyol	68551-65-5	0.7@22.0°C	A None, O None
Primary amyl acetate Propoxypropanol	628-63-7 1569-01-3	4.2 2.0	A 100.0 ppm 15 min STEL, A 50.0 ppm, O 100.0 ppm A None, O None
Propylene glycol monomethyl ether ac-	108-65-6	3.8	D 30.0 ppm 15 min TWA, A None, O None
etate	100 00 0	0.0	
Quinacridone pigment	1047-16-1	None	A 10.0 mg/m3 inhalable dust, A 3.0 mg/m3, O 15.0
			mg/m3 Total Dust PNOR, O 5.0 mg/m3 Respirable Dust,
			D 10.0 mg/m3 Total Dust
Red iron oxide light	1332-37-2	None	A 10.0 mg/m3 PNOR, A 3.0 mg/m3 Respirable Dust,
			A 5.0 mg/m3 Fe, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust
Stoddard solvent	8052-41-3	None	A 100.0 ppm, O 500.0 ppm TWA, D 100.0 ppm 15 min
	0002 0		STEL, D 50.0 ppm 8 & 12 hour TWA
Synthetic resin	NotAvail	None	A None, O None
T-butyl acetate	540-88-5	None	A 200.0 ppm, O 200.0 ppm
Titanium dioxide	13463-67-7	None	O 15.0 mg/m3 Total Dust, D 10.0 mg/m3 Total Dust, D 5.0
Taluana	100.00.0	22.0	mg/m3 Respirable Dust, A None
Toluene	108-88-3	22.0	A 20.0 ppm , O 300.0 ppm CEIL, O 500.0 ppm 10 min TWA, O 200.0 ppm, D 50.0 ppm 8 & 12 hour TWA Skin
Ultraviolet absorber	104810-47-1	None	A None, O None
Vm&p naphtha	8032-32-4	17.9@68.0 °F	A 300.0 ppm, D 100.0 ppm, O None
Xylene	1330-20-7	8.0@25.0 °C	A 150.0 ppm 15 min STEL, A 100.0 ppm, O 100.0 ppm,
			D 150.0 ppm 15 min STEL, D 100.0 ppm 8 & 12 hour
			TWA
Yellow iron oxide	51274-00-1	None	A 10.0 mg/m3, O 15.0 mg/m3

*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @ 20° C unless otherwise noted.

3. Hazards identification

Potential Health Effects:

Inhalation:

May cause nose and throat irritation. May cause nervous system depression, characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If this product contains or is mixed with an isocyanate activator/hardener, the following health effects may apply: Exposure to isocyanates may cause respiratory sensitization. This effect may be permanent. Symptoms include an asthma-like reaction with shortness of breath, wheezing, cough or permanent lung sensitization. This effect may be delayed for several hours after exposure. Repeated overexposure to isocyanates may cause a decrease in lung function, which may be permanent. Individuals with lung or breathing problems or prior reactions to isocyanates must not be exposed to vapors or spray mist of this product.

Ingestion:

May result in gastrointestinal distress.

Skin or eye contact:

May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.

Other Potential Health Effects in addition to those listed above:

1,6-hexamethylene diisocyanate

Overexposure may cause asthma-like reactions with shortness of breath, wheezing, cough, which may be permanent; or permanent lung sensitization. This effect may be delayed for several hours after exposure. The following medical conditions may be aggravated by exposure: asthma, skin disorders, respiratory disorders. Overexposure may cause damage to any of the following organs/systems: lungs, skin. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin.

2,4-pentanedione

2,4-pentanedione, a component of this product, is regulated by the U.S. EPA, under a significant new use rule. It is a violation of federal law to sell or use this product in consumer applications, including to private individuals, schools, and vocational schools. Can be absorbed through the skin in harmful amounts. Repeated exposures to high concentrations has caused adverse health effects in laboratory animals. These effects involved the central nervous system, immune system, and the red blood cell forming system. No effect was seen at 100 ppm. The odor is disagreeable at a few ppm. Repeated or prolonged skin contact may cause any of the following: irritation. Overexposure of this substance may cause effects on any of the following organs/systems: central nervous system, lungs, upper respiratory system, thymus.

4-chlorobenzotrifluoride

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: skin. Prolonged or repeated exposure may cause damage to any of the following organs/systems: kidneys, liver, thyroid. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin. Ingestion may cause any of the following: gastrointestinal irritation. Eye contact may cause any of the following: permanent eye injury. Inhalation may cause any of the following: stupor (central nervous system depression), respiratory tract irritation.

Acetone

The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.

Acrylic polymer-A

Skin or eye contact may cause any of the following: irritation.

Acrylic polymer-F

Skin contact may cause any of the following: mild irritation.

Aliphatic polyisocyanate resin

Overexposure may cause asthma-like reactions with shortness of breath, wheezing, cough, which may be permanent; or permanent lung sensitization. This effect may be delayed for several hours after exposure. The following medical conditions may be aggravated by exposure: asthma, skin disorders, respiratory disorders. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin.

Aromatic hydrocarbon

The following medical conditions may be aggravated by exposure: skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Butyl acetate

May cause abnormal liver function. The following medical conditions may be aggravated by exposure: respiratory system. Tests for embryotoxic activity in animals has been inconclusive. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

Carbon black

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease. WARNING: This chemical is known to the State of California to cause cancer.

Cumene

WARNING: This chemical is known to the State of California to cause cancer.

Ethyl acetate

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: eyes, respiratory system, skin. Tests in laboratory animals have shown effects on any of the following organs/systems: blood, kidneys, liver.

Ethylbenzene

Is an IARC, NTP or OSHA carcinogen. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. Studies in laboratory animals have shown reproductive, embryotoxic and developmental effects. WARNING: This chemical is known to the State of California to cause cancer.

Ethylene glycol monobutyl ether acetate

May destroy red blood cells. May cause abnormal kidney function. May cause temporary upper respiratory and/or lung irritation with cough, difficult breathing, or shortness of breath. The following medical conditions may be aggravated by exposure: central nervous system, gastrointestinal system, kidneys, liver, dermatitis. Can be absorbed through the skin in harmful amounts. Overexposure may cause damage to any of the following organs/systems: blood, kidneys, liver. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Heptane

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, respiratory system, skin. May cause central nervous system effects such as dizziness, headache, nausea, and loss of consciousness. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors. Aspiration may occur during swallowing or vomiting, resulting in lung damage.

Hydrotreated heavy naphtha (petroleum)

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Isopropyl alcohol

The following medical conditions may be aggravated by exposure: dermatitis, respiratory disease. Developmental toxicity was seen in rat's offspring at doses that were maternally toxic. Contact may cause skin irritation with discomfort or rash. Can be absorbed through the skin in harmful amounts. Contact will cause moderate to severe redness and swelling, itching, tingling sensation, painful burning. May cause injury to the cornea of the eyes. Prolonged or repeated exposure may cause damage to any of the following organs/systems: liver. Ingestion studies on laboratory animals showed that very high oral doses caused increased liver and kidney weights. Aspiration may occur during swallowing or vomiting, resulting in lung damage. May cause central nervous system depression with headache, stupor, uncoordinated or strange behavior, or unconsciousness. Irritating to the mouth, throat and stomach. May cause irritation of the respiratory tract, experienced as nasal discomfort and discharge, coughing and possibly accompanied by chest pain. Prolonged or repeated skin contact may cause drying, cracking, or irritation. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness. Swallowing significant amounts of substance could cause serious injury, even death.

Light yellow lemon yellow oxide pigment

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Methyl ethyl ketone

Material is irritating to mucous membranes and upper respiratory tract. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, respiratory system, skin. Prolonged or repeated overexposure may cause any of the following: conjunctivitis, dermatitis. High concentrations have caused embryotoxic effects in laboratory animals. Aspiration may occur during swallowing or vomiting, resulting in lung damage. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Methyl isoamyl ketone

Extremely high oral doses in laboratory animals have shown weight changes in various organs such as the liver, kidney and adrenal gland. In addition liver injury was observed.

N-butyl alcohol

May cause abnormal blood forming function with anemia. Liquid splashes in the eye may result in chemical burns.

Pigment red

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Poly(oxy-1,2-ethanediyl),.alpha.-[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy phenyl

The following medical conditions may be aggravated by exposure: jaundice, liver disease, allergies, kidney disorders, skin disorders. Skin contact may cause any of the following: allergic contact dermatitis.

Propoxypropanol

May cause moderate eye burning. Recurrent overexposure may result in liver and kidney injury.

Propylene glycol monomethyl ether acetate

Recurrent overexposure may result in liver and kidney injury.

Red iron oxide light

Long- term respiratory exposure of iron oxide may result in deposition of particles in the lung (benign siderosis).

Stoddard solvent

The following medical conditions may be aggravated by exposure: asthma, skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

T-butyl acetate

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, gastrointestinal system, liver, skin.

Titanium dioxide

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m3 respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m3 level are not relevant to the workplace. 'Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.'

Toluene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, respiratory system, skin. Can be absorbed through the skin in harmful amounts. Recurrent overexposure may result in liver and kidney injury. High airborne levels have produced irregular heart beats in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. WARNING: This chemical is known to the State of California to cause birth defects or other reproductive harm.

Ultraviolet absorber

The following medical conditions may be aggravated by exposure: jaundice, liver disease, allergies, kidney disorders, skin disorders. Skin contact may cause any of the following: allergic contact dermatitis.

Vm&p naphtha

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs, respiratory system, skin. This substance may cause damage to any of the following organs/systems: central nervous system, kidneys, liver, lungs, skin and eyes. Material may be harmful or fatal if swallowed.

Xylene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, cardiovascular system, central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. High exposures may produce irregular heart beats. Canada classifies Xylene as a developmental toxin as high exposures to xylenes in some animal studies have been reported to cause health effects on the developing fetus/embryo. These effects were often at levels toxic to the adult animal. The significance of these effects to humans is not known. Repeated or prolonged skin contact may cause any of the following: irritation, dryness, cracking of the skin.

4. First aid measures

First Aid Procedures:

Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

Skin or eye contact:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

5. Fire-fighting measures

Flash Point (Closed Cup):

See Section 11 for exact values.

Flammable Limits: LFL 0.5 % UFL 16.9 %

Extinguishing Media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

Fire Fighting Procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

Fire and Explosion Hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

6. Accidental release measures

Procedures for cleaning up spills or leaks:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. If material does not contain or is not mixed with an isocyanate activator/hardener: Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly. If the material contains, or is mixed with an isocyanate activator/hardener: Wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C), eye protection, gloves and protective clothing. Pour liquid decontamination solution over the spill and allow to sit at least 10 minutes. Typical decontamination solutions for isocyanate containing materials are: 20% Surfactant (Tergitol TMN 10) and 80% Water OR 0-10% Ammonia, 2-5% Detergent and Water (balance). Pressure can be generated. Do not seal waste containers for 48 hours to allow C02 to vent. After 48 hours, material may be sealed and disposed of properly.

Ecological information:

There is no data available on the product. The product should not be allowed to enter drains, water courses or the soil.

7. Handling and storage

Precautions to be taken in handling and storing:

Observe label precautions. If combustible (flashpoint between 38-93 deg C or 100 - 200 deg F), keep away from heat, sparks and flame. If flammable (flashpoint less than 38 deg C or 100 deg F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than - 8 deg C or 20 deg F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 49 deg C or 120 deg F. If product is waterbased, do not freeze.

Other precautions:

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves. Combustible dust clouds may be created where operations produce fine material (dust). Avoid formation of significant deposits of material as they may become airborne and form combustible dust clouds. Handling and processing operations should be conducted in accordance with best practices (e.g.NFPA-654).

8. Exposure controls/personal protection

Ventilation:

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

Respiratory protection:

Do not breathe vapors or mists. If this product contains isocyanates or is used with an isocyanate activator/hardener, wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C) while mixing activator/hardener with paint, during application and until all vapors and spray mist are exhausted. If product does not contain or is not mixed with an isocyanate activator/hardener, a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH TC-23C) and particulate filter (NIOSH TC-84A) may be used. Follow respirator manufacturers directions for respirator use. Do not permit anyone without protection in the painting area. Individuals with history of lung or breathing problems or prior reaction to isocyanates should not use or be exposed vapor or spray mist if product contains or is mixed with isocyanate activators/hardeners.

Protective equipment:

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

Skin and body protection:

Neoprene gloves and coveralls are recommended.

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

9. Physical and chemical properties

7 • • • • • • • • • • •	
Evaporation rate	Slower than Ether
Water solubility	NIL
Vapour density	Heavier than air
Approx. Boiling Range (° C)	55 – 152 ° C
Approx. Freezing Range (° C)	-99 – -65 ° C
Gallon Weight (lbs/gal)	6.92668 - 15.3138
Specific Gravity	0.83 - 1.84
Percent Volatile By Volume	12.63 - 100.00
Percent Volatile By Weight	9.96 - 99.99
Percent Solids By Volume	0.00 - 87.37
Percent Solids By Weight	0.00 - 90.04

10. Stability and reactivity

Stability:

Stable

Incompatibility (materials to avoid):

None reasonably foreseeable

Hazardous decomposition products:

CO, C02, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

Hazardous Polymerization:

Will not occur.

Sensitivity to Static Discharge:

For flammable materials (flashpoint less than 38 deg C or 100 deg F) and combustibles (flashpoint between 38- 93 deg C or 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

Sensitivity to Mechanical Impact:

None known.

11. Additional Information

193S[™] 1,6-hexamethylene diisocyanate(0.1%*@), Aliphatic polyisocyanate resin, Butyl acetate, Ethyl acetate, Ethylene glycol monobutyl ether acetate(4%*@) GAL WT: 9.01 WT PCT SOLIDS: 74.99 VOL PCT SOLIDS: 70.05 SOLVENT DENSITY: 7.53 VOC LE: 2.3 VOC AP: 2.3 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO 1945[™] 2-ethylhexyl acetate, Aliphatic polyisocyanate resin, Butyl acetate, Ethyl acetate GAL WT: 9.05 WT PCT SOLIDS: 75.00 VOL PCT SOLIDS: 69.53 SOLVENT DENSITY: 7.43 VOC LE: 2.3 VOC AP: 2.3 FLASH POINT: 20 °F to below 73 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

3401S[™] 1,2,4-trimethyl benzene(1%*), Acrylic polymer-G, Aromatic hydrocarbon, Butyl acetate, Ethyl 3-ethoxy propionate, Ethylbenzene(0.8%*@), Ethylene glycol monobutyl ether acetate(11%*@), Methyl ethyl ketone, Propylene glycol monomethyl ether acetate, Toluene(10%*@), Xylene(3%*@) GAL WT: 7.27 WT PCT SOLIDS: 3.55 VOL PCT SOLIDS: 2.75 SOLVENT DENSITY: 7.21 VOC LE: 7.0 VOC AP: 7.0 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

34205[™] 4-chlorobenzotrifluoride, Acetone, Acrylic polymer-B, Acrylic resin, Butyl acetate, Isopropyl alcohol, Methyl acetate, Methyl amyl ketone, Polyester resin-B, Synthetic resin GAL WT: 8.56 WT PCT SOLIDS: 53.98 VOL PCT SOLIDS: 49.30 SOLVENT DENSITY: 7.74 VOC LE: 2.6 VOC AP: 2.1 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

34305[™] 2-ethylhexyl acetate, Acetone, Acrylic polymer-B, Dimethyl glutarate, Hydrotreated heavy naphtha (petroleum), Isopropyl alcohol, Methyl amyl ketone GAL WT: 8.02 WT PCT SOLIDS: 52.26 VOL PCT SOLIDS: 44.69 SOLVENT DENSITY: 6.94 VOC LE: 3.7 VOC AP: 3.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

3440S[™] Acrylic polymer-B, Butanedioic acid, dimethyl ester, Butyl acetate, Dimethyl glutarate, Ethylene glycol monobutyl ether acetate(3%*@), Methyl amyl ketone, Methyl ethyl ketone, Toluene(4%*@) GAL WT: 8.17 WT PCT SOLIDS: 53.35 VOL PCT SOLIDS: 46.68 SOLVENT DENSITY: 7.17 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 20 °F to below 73 °F H: 1 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

34805[™] 2-ethylhexyl acetate, Acetone, Acrylic polymer-B, Dimethyl glutarate, Hydrotreated heavy naphtha (petroleum), Isopropyl alcohol, Methyl amyl ketone GAL WT: 8.02 WT PCT SOLIDS: 52.26 VOL PCT SOLIDS: 44.69 SOLVENT DENSITY: 6.94 VOC LE: 3.7 VOC AP: 3.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

3895[™] 2,4-pentanedione, Dibutyl tin dilaurate GAL WT: 8.14 WT PCT SOLIDS: 1.00 VOL PCT SOLIDS: 0.94 SOLVENT DENSITY: 8.14 VOC LE: 8.1 VOC AP: 8.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

501H[™] Acrylic polymer-F, Butyl acetate, Carbon black(0.6%), Methyl amyl ketone GAL WT: 8.23 WT PCT SOLIDS: 52.25 VOL PCT SOLIDS: 44.96 SOLVENT DENSITY: 7.14 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

502H[™] Acrylic polymer-F, Butyl acetate, Methyl amyl ketone, Propylene glycol monomethyl ether acetate, Red iron oxide light, Toluene(1%*@) GAL WT: 14.00 WT PCT SOLIDS: 74.27 VOL PCT SOLIDS: 48.47 SOLVENT DENSITY: 7.01 VOC LE: 3.6 VOC AP: 3.6 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

504H[™] 1,2,4-trimethyl benzene(1%*), Acrylic polymer-F, Aromatic hydrocarbon, Butyl acetate, Methyl amyl ketone, Phthalocyanine blue pigment, Propylene glycol monomethyl ether acetate, Toluene(1%*@) GAL WT: 8.63 WT PCT SOLIDS: 50.55 VOL PCT SOLIDS: 43.86 SOLVENT DENSITY: 7.60 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

505H[™] 1,2,4-trimethyl benzene(3%*), Acrylic polymer-F, Aromatic hydrocarbon, Butyl acetate, Carbon black(4.4%), Cumene(0.1%*@), Methyl amyl ketone, Toluene(2%*@) GAL WT: 8.27 WT PCT SOLIDS: 48.52 VOL PCT SOLIDS: 41.36 SOLVENT DENSITY: 7.52 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

506H[™] 1,2,4-trimethyl benzene(1%*), Acrylic polymer-F, Aromatic hydrocarbon, Butyl acetate, Methyl amyl ketone, Phthalocyanine green, Toluene(2%*@) GAL WT: 8.22 WT PCT SOLIDS: 44.36 VOL PCT SOLIDS: 33.34 SOLVENT DENSITY: 7.06 VOC LE: 4.6 VOC AP: 4.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

507H[™] 1,2,4-trimethyl benzene(1%*), Acrylic polymer-F, Aromatic hydrocarbon, Butyl acetate, Ethylbenzene(0.2%*@), Methyl amyl ketone, Phthalocyanine blue pigment, Propylene glycol monomethyl ether acetate, Toluene(1%*@) GAL WT: 8.60 WT PCT SOLIDS: 48.11 VOL PCT SOLIDS: 40.74 SOLVENT DENSITY: 7.54 VOC LE: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

509H[™] Acrylic polymer-F, Butyl acetate, C.i. pigment red 254, Methyl amyl ketone, Propylene glycol monomethyl ether acetate GAL WT: 9.16 WT PCT SOLIDS: 53.24 VOL PCT SOLIDS: 44.43 SOLVENT DENSITY: 8.08 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

513H[™] 1,2,4-trimethyl benzene(1%*), Acrylic polymer-F, Aromatic hydrocarbon, Barium sulfate, Butyl acetate, Ethylbenzene(0.1%*@), Methyl amyl ketone, Pigment red, Pigment red 202, Propylene glycol monomethyl ether acetate, Toluene(2%*@) GAL WT: 8.57 WT PCT SOLIDS: 41.70 VOL PCT SOLIDS: 34.90 SOLVENT DENSITY: 7.83 VOC LE: 5.0 VOC AP: 5.0 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

514H[™] 2-methyl butyl acetate, Acrylic polymer-F, Butyl acetate, Methyl amyl ketone, Primary amyl acetate, Quinacridone pigment GAL WT: 8.46 WT PCT SOLIDS: 47.13 VOL PCT SOLIDS: 38.11 SOLVENT DENSITY: 7.24 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

515H[™] Acrylic polymer-F, Butyl acetate, Methyl amyl ketone, Propylene glycol monomethyl ether acetate, Toluene(2%*@), Yellow iron oxide GAL WT: 12.94 WT PCT SOLIDS: 67.62 VOL PCT SOLIDS: 45.37 SOLVENT DENSITY: 7.68 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO 516H[™] Acrylic polymer-F, Aluminum hydroxide, Amorphous silica-A, Butyl acetate, Methyl amyl ketone, Propylene glycol monomethyl ether acetate, Titanium dioxide(55.4%) GAL WT: 15.31 WT PCT SOLIDS: 77.96 VOL PCT SOLIDS: 55.80 SOLVENT DENSITY: 7.65 VOC LE: 3.4 VOC AP: 3.4 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

518H[™], 1,2,4-trimethyl benzene(3%*), Acrylic polymer-F, Aromatic hydrocarbon, Butyl acetate, Carbazole violet pigment, Cumene(0.2%*@), Ethylbenzene(0.3%*@), Methyl amyl ketone, Propylene glycol monomethyl ether acetate, Xylene(1%*@) GAL WT: 8.41 WT PCT SOLIDS: 53.52 VOL PCT SOLIDS: 47.63 SOLVENT DENSITY: 7.47 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

519H[™] 1,2,4-trimethyl benzene(3%*), Acrylic polymer-C, Aromatic hydrocarbon, Butyl acetate, C.i. pigment blue 60, Cumene(0.2%*@), Methyl amyl ketone, Propylene glycol monomethyl ether acetate GAL WT: 8.31 WT PCT SOLIDS: 49.15 VOL PCT SOLIDS: 42.67 SOLVENT DENSITY: 7.61 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

522H[™] 1,2,4-trimethyl benzene(4%*), Acrylic polymer-E, Aluminum(25%*), Aromatic hydrocarbon, Butyl acetate, Cumene(0.2%*@), Hydrotreated heavy naphtha (petroleum), N-butyl alcohol(2%*), Propylene glycol monomethyl ether acetate, Stoddard solvent GAL WT: 9.32 WT PCT SOLIDS: 51.06 VOL PCT SOLIDS: 38.11 SOLVENT DENSITY: 7.23 VOC LE: 4.6 VOC AP: 4.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

525H[™] 1,2,4-trimethyl benzene(1%*), 2-methyl butyl acetate, Acrylic polymer-F, Aromatic hydrocarbon, Butyl acetate, Iron oxide, Methyl amyl ketone, Primary amyl acetate GAL WT: 9.54 WT PCT SOLIDS: 52.89 VOL PCT SOLIDS: 37.74 SOLVENT DENSITY: 7.23 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

527H[™] Acrylic polymer-F, Barium sulfate, Butyl acetate, Methyl amyl ketone, Perylene maroon, Propylene glycol monomethyl ether acetate, Toluene(3%*@) GAL WT: 8.81 WT PCT SOLIDS: 44.06 VOL PCT SOLIDS: 36.09 SOLVENT DENSITY: 7.97 VOC LE: 4.9 VOC AP: 4.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

528H[™] Acrylic polymer-F, Azo yellow pigment, Butyl acetate, Methyl amyl ketone, Propylene glycol monomethyl ether acetate GAL WT: 9.03 WT PCT SOLIDS: 49.62 VOL PCT SOLIDS: 41.52 SOLVENT DENSITY: 23.03 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

529H[™] Acrylic polymer-F, Butyl acetate, Isoindolinone pigment, Methyl amyl ketone, Propylene glycol monomethyl ether acetate GAL WT: 9.43 WT PCT SOLIDS: 51.48 VOL PCT SOLIDS: 40.48 SOLVENT DENSITY: 7.97 VOC LE: 4.6 VOC AP: 4.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

542H[™] 2-methyl butyl acetate, Acrylic polymer-F, Aromatic hydrocarbon, Methyl amyl ketone, Primary amyl acetate, Quinacridone pigment GAL WT: 8.30 WT PCT SOLIDS: 48.81 VOL PCT SOLIDS: 40.93 SOLVENT DENSITY: 7.20 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

545H[™] 1,2,4-trimethyl benzene(2%*), 2-methyl butyl acetate, Acrylic polymer-F, Aromatic hydrocarbon, Butyl acetate, Cumene(0.1%*@), Light yellow lemon yellow oxide pigment, Methyl amyl ketone, Primary amyl acetate GAL WT: 9.32 WT PCT SOLIDS: 54.32 VOL PCT SOLIDS: 41.04 SOLVENT DENSITY: 7.23 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

551H[™] Acrylic polymer-F, Butyl acetate, C.i. pigment yellow 138, Ethylbenzene(0.3%*@), Methyl amyl ketone, Propylene glycol monomethyl ether acetate, Titanium dioxide(1.4%), Xylene(1%*@) GAL WT: 9.65 WT PCT SOLIDS: 53.11 VOL PCT SOLIDS: 41.08 SOLVENT DENSITY: 7.99 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

569H[™] Acrylic polymer-F, Butyl acetate, Methyl amyl ketone, Monoazo pigment, Propylene glycol monomethyl ether acetate GAL WT: 9.67 WT PCT SOLIDS: 59.60 VOL PCT SOLIDS: 49.65 SOLVENT DENSITY: 7.77 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 1 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

577H[™] 1,2,4-trimethyl benzene(2%*), Acrylic polymer-C, Aromatic hydrocarbon, Butyl acetate, Cumene(0.1%*@), Ethyl acetate, Ethylene glycol monobutyl ether acetate(10%*@), Methyl amyl ketone, Methyl ethyl ketone, Organoclay, Polyester resin-D GAL WT: 8.05 WT PCT SOLIDS: 33.41 VOL PCT SOLIDS: 27.47 SOLVENT DENSITY: 7.40 VOC LE: 5.4 VOC AP: 5.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

590H[™] 1,2,4-trimethyl benzene(3%*), Acrylic polymer-E, Aluminum(24%*), Aromatic hydrocarbon, Butyl acetate, Cumene(0.2%*@), Hydrotreated heavy naphtha (petroleum), N-butyl alcohol(2%*), Propylene glycol monomethyl ether acetate GAL WT: 9.18 WT PCT SOLIDS: 49.62 VOL PCT SOLIDS: 35.36 SOLVENT DENSITY: 7.16 VOC LE: 4.6 VOC AP: 4.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

86855[™] Ethyl acetate, Ethylene glycol monobutyl ether acetate(40%*@), Methyl ethyl ketone GAL WT: 7.55 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.57 VOC LE: 7.5 VOC AP: 7.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8840STM 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Butyl acetate, Dimethyl glutarate, Hydrotreated heavy naphtha (petroleum), Isopropyl alcohol, Methyl amyl ketone GAL WT: 7.96 WT PCT SOLIDS: 52.00 VOL PCT SOLIDS: 44.94 SOLVENT DENSITY: 6.92 VOC LE: 3.7 VOC AP: 3.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8940S[™] Ethyl acetate, Methyl amyl ketone, Poly(oxy-1,2-ethanediyl),.alpha.-[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy phenyl, Polyester resin-B, Ultraviolet absorber GAL WT: 8.71 WT PCT SOLIDS: 90.04 VOL PCT SOLIDS: 87.37 SOLVENT DENSITY: 6.89 VOC LE: 0.9 VOC AP: 0.9 FLASH POINT: 100 ° F

MSDS 22 Imron ® 6000 Polyurethane Enamel

141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8950STM Ethyl 3-ethoxy propionate, Ethyl acetate, Ethylbenzene(0.7%*@), Methyl ethyl ketone, Polyester resin-D, Xylene(3%*@) GAL WT: 9.28 WT PCT SOLIDS: 80.96 VOL PCT SOLIDS: 75.78 SOLVENT DENSITY: 7.32 VOC LE: 1.8 VOC AP: 1.8 FLASH POINT: 20 °F to below 73 °F H: 1 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

8960S[™] Acrylic polymer-F, Amorphous silica-B, Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Poly(oxy-1,2-ethanediyl),.alpha.-[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy phenyl, Polyol, Ultraviolet absorber GAL WT: 8.00 WT PCT SOLIDS: 67.20 VOL PCT SOLIDS: 60.96 SOLVENT DENSITY: 6.74 VOC LE: 2.6 VOC AP: 2.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8970S[™] Acetone, Ethyl 3-ethoxy propionate, Ethyl acetate, Methyl ethyl ketone GAL WT: 6.93 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 6.93 VOC LE: 7.2 VOC AP: 3.9 FLASH POINT: Below 20 ° F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8975S[™] Acrylic polymer-D, Ethylbenzene(0.2%*@), Isopropyl alcohol, N-butyl alcohol(6%*), Toluene(5%*@), Vm&p naphtha GAL WT: 8.21 WT PCT SOLIDS: 61.50 VOL PCT SOLIDS: 51.52 SOLVENT DENSITY: 6.43 VOC LE: 3.2 VOC AP: 3.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8989S[™] 2,4-pentanedione, Dibutyl tin dilaurate GAL WT: 8.16 WT PCT SOLIDS: 5.00 VOL PCT SOLIDS: 4.68 SOLVENT DENSITY: 8.14 VOC LE: 7.8 VOC AP: 7.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

EZ-3460S[™] 2-ethylhexyl acetate, Acetone, Acrylic polymer-B, Acrylic resin, Butyl acetate, Heptane, Hydrotreated heavy naphtha (petroleum), Isopropyl alcohol, Methyl amyl ketone, Methyl isoamyl ketone GAL WT: 7.87 WT PCT SOLIDS: 49.52 VOL PCT SOLIDS: 41.99 SOLVENT DENSITY: 6.82 VOC LE: 3.8 VOC AP: 3.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

RKP27687[™] Acetone, Amorphous silica-A, Polycaprolactone diol, Polyester resin-A, Propoxypropanol, T-butyl acetate GAL WT: 8.69 WT PCT SOLIDS: 56.70 VOL PCT SOLIDS: 47.44 SOLVENT DENSITY: 7.16 VOC LE: 3.6 VOC AP: 3.5 VOC LE (TBAC): 0.9 VOC AP (TBAC): 0.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

RKP33093[™] Acetone, Amorphous silica - precipitated, Butyl acetate, Ethylbenzene(0.4%*@), Methyl acetate, Methyl ethyl ketone, Polyester resin-C, Toluene(1%*@), Xylene(1%*@) GAL WT: 8.93 WT PCT SOLIDS: 50.92 VOL PCT SOLIDS: 41.99 SOLVENT DENSITY: 7.54 VOC LE: 2.1 VOC AP: 1.2 FLASH POINT: Below 20 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

VGP28269[™] Butyl acetate, Dibutyl tin dilaurate, Methyl amyl ketone GAL WT: 7.06 WT PCT SOLIDS: 1.15 VOL PCT SOLIDS: 0.93 SOLVENT DENSITY: 7.06 VOC LE: 7.0 VOC AP: 7.0 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

Footnotes:

TSCA: in compliance In compliance with TSCA Inventory requirements for commercial purposes.

ACGIH American Conference of Governmental Industrial Hygienists.

IARC International Agency for Research on Cancer.

NTP National Toxicology Program.

OSHA Occupational Safety and Health Administration.

PNOR Particles not otherwise regulated.

PNOC Particles not otherwise classified.

STEL Short term exposure limit.

TWA Time-weighted average.

* VOC less exempt (theoretical) and VOC as packaged (theoretical) are based upon the VOC of the packaged material at the point of manufacture.

TBAC is not universally recognized as an exempt solvent.

Users should consult the applicable regulations for their region.

All products denoted with TM or (R) are trademarks or registered trademarks of E. I. du Pont de Nemours and Company or its affiliates.

* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Listed as a Clean Air Act Hazardous Air Pollutant.

= EPCRA Section 302 - Extremely hazardous substances.

Notice:

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager: Refinish Sales Prepared by: Y. B. Yarbrough