

**GRAND PACIFIC PETROCHEMICAL CORP**

10TH FL, 1 NANJING E RD, SEC 4, TAIPEI 105 TW

**N200SL(f2)**

Polyamide 66 (PA66), "Gramid", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	0.71	V-2	4	0	130	75	85
	1.5	V-2	3	0	130	75	85
	3.0	V-2	3	0	130	75	85

Comparative Tracking Index (CTI): **0**

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): **35**Volume Resistivity (10<sup>8</sup> ohm-cm) : **13**

High-Voltage Arc Tracking Rate (HVTR): -

High Volt, Low Current Arc Resis (D495): **4**

Dimensional Stability (%): -

(f2) - Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2012-09-14

Last Revised: 2016-07-29

© 2014 UL LLC

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.71	V-2 (ALL)
			1.5	V-2 (ALL)
			3.0	V-2 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	0.71	960
			3.0	960
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	0.71	960
			3.0	725
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m <sup>2</sup>	-	-
ISO Izod Impact	ISO 180	kJ/m <sup>2</sup>	-	-
ISO Charpy Impact	ISO 179-2	kJ/m <sup>2</sup>	-	-

© 2014 UL LLC

The materials covered in this database are incomplete in certain constructional features or restricted in performance capabilities and are intended for use as components of complete equipment submitted for investigation rather than for direct separate installation in the field. THE FINAL ACCEPTANCE OF THE COMPONENT IS DEPENDENT UPON ITS INSTALLATION AND USE IN COMPLETE PRODUCTS SUBMITTED TO UNDERWRITERS LABORATORIES.

Notice of Disclaimer