

Automotive Catalog

2ply 2mil	NANO CERAMIC IR					Solar Energy		
Name	VLT (%)	UVR	IR-Rejection	TSER	Glare Reduction	T	A	R
Quantum 05%	5%	99.9	83	58	93	13	82	5
Quantum 15%	15%	99.9	81	55	84	19	76	5
Quantum 20%	20%	99.9	83	55	80	19	76	5
Quantum 35%	35%	99.9	85	49	59	28	66	6
Quantum 50%	50%	99.9	84	47	44	33	60	6
Quantum 70%	70%	99.9	93.8	41	60	42	51	6

2ply 1.5mil	COLOR STABLE CARBON					Solar Energy		
Name	VLT (%)	UV-Rejection	IR-Rejection	TSER	Glare Reduction	T	A	R
Optic 05%	5%	99.9	32	50	94	34	60	6
Optic 15%	15%	99.9	34	49	88	36	58	6
Optic 20%	20%	99.9	34	45	77	40	54	6
Optic 35%	35%	99.9	32	41	65	46	49	6
Optic 40%	40%	99.9	34	38	61	60	58	6
Optic 50%	50%	99.9	31	35	47	54	46	6

2ply 1.5mil	DYED EXTRUDED NON REFLECTIVE					Solar Energy		
Name	VLT (%)	UV-Rejection	IR-Rejection	TSER	Glare Reduction	T	A	R
Shadow 05%	5%	99.9	11	47	94	41	54	5
Shadow 15%	15%	99.9	10	45	90	53	27	6
Shadow 20%	20%	99.9	12	39	79	48	47	5
Shadow 35%	35%	99.9	10	35	60	54	40	6
Shadow 40%	40%	99.9	10	33	54	56	39	5
Shadow 50%	50%	99.9	8	27	50	60	35	5