



Xuchang DADA Technology Co.,Ltd

Address: NO.612 HUAYUAN COUNTRY,SHIGU TOWN,CHANGGE CITY,HENAN PROVINCE,CHINA

Phone: +86-13603031941

E-mail: george@dadataec.com

Technical Information

Materials & Item		High Alumina Bricks			
Category		SK 36	SK 37	SK 38	SK 40
Chemical Composition	Al ₂ O ₃ % (≥)	55	65	70	82
	Fe ₂ O ₃ % (≤)	2.0	2.0	2.0	2.0
Deformation Temperature under loading (0.2 Mpa) °C (≥)		1350	1400	1450	1500
Porosity %		20--23	20--23	20--22	18--20
Bulk Density g/cm ³		2.25--2.40	2.30--2.50	2.65--2.85	2.7--2.90
Compressive Strength at 20°C (≥)		45	50	60	70