



Galal Paper

Technical Data Sheet Index

1	CB150J	2
2	CB200J	3
3	CB250J	4
4	CB300J	5
5	CB400J	6
6	CB500J	7
7	SCB200J	8
8	SCB250J	9
9	SCB300J	10
10	SCB400J	11
11	SCB500J	12
12	SCB600J	13
13	SCB700J	14
14	SCB800J	15
15	CBZ200J	16
16	CBZ250J	17
17	CBZ300J	18



TECHNICAL SPECIFICATIONS

Core board 150 Joule/m²

Product code	CB150J			
Roll Width	From 7.9 cm To 172 cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	250 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.55
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.5-1.6
Plybond	j/m ²	EN ISO 16260	Not Less Than	150
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	8.0

Product Code	CB150J			
Roll Width	From 7.9 cm To 172 cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.55
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.5-1.6
Plybond	j/m ²	EN ISO 16260	Not Less Than	150
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	8.5

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Core board 200 Joule/m²

Product code	CB200J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	200
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	8.0

Product Code	CB200J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	200
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	8.5

Rev. 08-Jul-2025

TECHNICAL SPECIFICATIONS

Core board 250 Joule/m²

Product code	CB250J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	250
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	9.0

Product Code	CB250J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	250
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	10.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Core board 300 Joule/m²

Product code	CB300J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	300
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	10.5

Product Code	CB300J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	300
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.1
RCT index	Nm/g		Not Less Than	11.5

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Core board 400 Joule/m²

Product code	CB400J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	400
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.8
RCT index	Nm/g		Not Less Than	15.0

Product Code	CB400J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	400
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.8
RCT index	Nm/g		Not Less Than	16.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Core board 500 Joule/m²

Product code	CB500J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	500
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.9
RCT index	Nm/g		Not Less Than	16.0

Product Code	CB500J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	500
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.9
RCT index	Nm/g		Not Less Than	17.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 200 Joule/m²

Product code	SCB200J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	200
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.6
RCT index	Nm/g		Not Less Than	11.5

Product Code	SCB200J			
Roll Width	From 5 cm To 7.9 cm.			
External Diameter	From 7.9 cm To 195cm.			
Core inner diameter	Min. 110 cm Max. 125 cm.			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	200
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.4
RCT index	Nm/g		Not Less Than	12.5

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 250 Joule/m²

Product code	SCB250J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	250
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.3
RCT index	Nm/g		Not Less Than	12.5

Product Code	SCB250J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	250
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.3
RCT index	Nm/g		Not Less Than	13.5

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 300 Joule/m²

Product code	SCB300J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	300
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.9
RCT index	Nm/g		Not Less Than	14.0

Product Code	SCB300J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	300
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.9
RCT index	Nm/g		Not Less Than	15.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 400 Joule/m²

Product code	SCB400J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	400
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.9
RCT index	Nm/g		Not Less Than	16.0

Product Code	SCB400J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	400
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.9
RCT index	Nm/g		Not Less Than	17.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 500 Joule/m²

Product code	SCB500J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	500
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.2
RCT index	Nm/g		Not Less Than	17.0

Product Code	SCB500J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	500
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.2
RCT index	Nm/g		Not Less Than	18.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 600 Joule/m²

Product code	SCB600J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	600
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.4
RCT index	Nm/g		Not Less Than	18.0

Product Code	SCB600J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	600
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.4
RCT index	Nm/g		Not Less Than	19.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 700 Joule/m²

Product code	SCB700J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	700
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.4
RCT index	Nm/g		Not Less Than	19.0

Product Code	SCB700J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	700
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.4
RCT index	Nm/g		Not Less Than	20.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Special Core board 800 Joule/m²

Product code	SCB800J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.35-1.45
Plybond	j/m ²	EN ISO 16260	Not Less Than	800
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.4
RCT index	Nm/g		Not Less Than	20.5

Product Code	SCB800J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	EN ISO 534	± 5%	1.35
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.25-1.4
Plybond	j/m ²	EN ISO 16260	Not Less Than	800
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			2.5
RCT index	Nm/g		Not Less Than	21.5

Rev. 08-Jul-2025

TECHNICAL SPECIFICATIONS

Core board Sized 200 Joule/m²

Product code	CBZ200J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	EN ISO 16260	Not Less Than	200
Cobb 60'	g/m ²	EN ISO 535		per request
Moisture	%	EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	8.0

Product Code	CBZ200J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	UNI EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	UNI EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	UNI EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	UNI 9439	Not Less Than	200
Cobb 60'	g/m ²	EN ISO 535		per request
Moisture	%	UNI EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	8.5

Rev. 08-Jul-2025

TECHNICAL SPECIFICATIONS

Core board Sized 250 Joule/m²

Product code	CBZ250J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	UNI EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	UNI EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	UNI EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	UNI 9439	Not Less Than	250
Cobb 60'	g/m ²	EN ISO 535		per request
Moisture	%	UNI EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	10.0

Product Code	CBZ250J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	UNI EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	UNI EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	UNI EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	UNI 9439	Not Less Than	250
Cobb 60'	g/m ²	EN ISO 535		per request
Moisture	%	UNI EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	11.0

Rev. 08-Jul-2025



TECHNICAL SPECIFICATIONS

Core board Sized 300 Joule/m²

Product code	CBZ300J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	UNI EN ISO 536	± 5%	200 To 315
Bulk	cm ³ /g	UNI EN ISO 534	± 5%	1.45
Bulk range	cm ³ /g	UNI EN ISO 534	± 5%	1.4-1.5
Plybond	j/m ²	UNI 9439	Not Less Than	300
Cobb 60'	g/m ²	EN ISO 535		per request
Moisture	%	UNI EN ISO 287	±2	6
Burst index	Kpa/grammage			1.0
RCT index	Nm/g		Not Less Than	10.5

Product Code	CBZ300J			
Roll Width	From 7.9 cm To 195cm.			
External Diameter	Min. 110 cm Max. 125 cm.			
Core inner diameter	7.6 cm , 10 cm			
Packaging Details	Roll(s) Will be labeled by descriptive label with Product type, Substance, Roll(s) Code and Roll(s) width; each Roll(s) is wrapped up in stretch wrap film.			
Tech. Specs.	Unit	Deter. Method	Tolerance	Sample
Basis Weight (GSM)	g/m ²	UNI EN ISO 536	± 5%	350 To 600
Bulk	cm ³ /g	UNI EN ISO 534	± 5%	1.40
Bulk range	cm ³ /g	UNI EN ISO 534	± 5%	1.3-1.5
Plybond	j/m ²	UNI 9439	Not Less Than	300
Cobb 60'	g/m ²	EN ISO 535		per request
Moisture	%	UNI EN ISO 287	±2	6
Burst index	Kpa/grammage			1.1
RCT index	Nm/g		Not Less Than	11.5

Rev. 08-Jul-2025