



Ultimate Sustainable Solutions

GREY SCALE & BURN TEST

GREY SCALE TEST

ASTM D2565-99 (Reapproved 2008),
Standard Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications
Xenon Arc Exposure, Cycle 1, 500 hours

RESULTS:

Brown Jarrah: Average grey scale 4.0
Weathered Grey: Average grey scale 4.5

BURN TEST RESULTS:

ANSI/UL94-2013 (R2017) – Horizontal Burn Test – Pass
ANSI/UL94-2018 section 8 – Vertical Burn Test – Not Passed



MCX Group Pty Ltd.
Ph: +613 9982 4456
Email: info@mcxmaterials.com

Australia:
Level 2 Riverside Quay
1 Southbank Boulevard
Southbank, Victoria, Australia, 3006

