HERMETIC™ Flake

Flooring System















<u>elite crete systems</u>

Engineered High Performance Surfaces & Flooring

HERMETIC™ Flake Floor is a durable, seamless, chemical resistant floor providing adjustable levels of slight texture and color to match any design theme or surroundings.

TYPICAL AREAS OF USE

- Public areas
- · Grocery stores
- Airports
- Showrooms
- Retail
- · Theme parks
- Hospitality
- Hospitals
- Educational
- · Automobile showrooms


ADVANTAGES

- Ease of maintenance
- Aesthetic improvements
- · Hygienic seamless finish
- · Hard and abrasion resistant
- VOC free CA 01350 air quality compliant
- · Stain and chemical resistant
- · Anti-microbial
- · Satin or gloss finish
- Fast set available for quicker turn around time

SPECIFICATION OVERVIEW

- Name: HERMETIC™ Flake Floor
- Surface preparation and detailed application instructions per manufacturer
- Manufacturer: Elite Crete Systems, Inc. +1-219-465-7671

SAMPLE COLOR CHART



NOTE: The colors depicted on this technical document may not illustrate the exact color. Contact a technical support representative for a more accurate color sample. Custom colors availible upon request.

PHYSICAL PROPERTIES

(@ 73°F / 23°C, 7 day ambient cure as a coating)

| PROPERTY | TEST | RESULT |
|------------------------------|----------------------|-------------------------------|
| VOC Content | N/A | 0 g/l |
| Shore D Hardness | ASTM D-2240 | 77 to 81 |
| Water Absorption (2hr boil) | ASTM D-570 | 0.12 % |
| Toxicity | N/A | None* |
| Heat Distortion Temperature | ASTM D-648 | 129 F / 54 C |
| Compressive Strength | ASTM D-695 | 11,900-13,400 psi |
| Tensile Strength | ASTM D-638 | 2,100-4,200 psi |
| Flexural Strength | ASTM D-790 | 4,500-6,400 psi |
| Abrasion Resistance ** | ASTM D-4060 | 9-30 mg loss |
| Slant Shear | ASTM C-882 | 100% concrete failure |
| Flammability | ASTM D-635 | Self-extinguishing |
| Flame Spread Rate (NFPA 101) | ASTM E-84 | Class A |
| Elongation at Break | ASTM D-638 | 4-6 % |
| Chemical Resistance | Contact technical | representative for chart |
| Coefficient of Friction | Adjusted per require | ment. Generally 0.50 to 0.80+ |
| COF Guidelines: | ADA Flat Surfaces | 0.60 |
| | ADA Inclined Surface | es 0.80 |
| | OSHA | 0.50 |
| | NFPA | 0.80 |
| | | |







6 Old Orchard Lane, Unit 100 Kingston, MA 02364 781-214-0333 Office 781-636-1118 Fax contactus@royalepoxyfloors.com www.royalepoxyfloors.com

The information herein is general information to assist our customers in determining whether our products are suitable for their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers should inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products for. Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability or fitness for a particular purpose, nor is replacement of our materials and in no event shall we be liable for incidental or consequential damages.