

| Properties | Value | Unit |
|---|---------------------------|------|
| Fire Endurance | 1-4 | Hour |
| Smoke Spread Index | 5 | - |
| Flame Spread Index | 0 | - |
| Combustion Performance | Noncombustible material | - |
| | Reaction to fire-Class A1 | - |
| Thermal Conductivity (Average Temperature:20℃) | ≤0.034 | W/m |
| Melting Point | >1150 | ℃ |

Test Standard

AS 1530.4-1997/ISO 834
ASTM E119/JIS A 1304
BS 476:Pt22

ASTM E84
UL 723

ASTM E84
UL 723

EN ISO 1182
GB/T 5464-1999

EN 13501-1
GB 8624-2006

ASTM C518
GB/T 19686-2005

-