

Product Testing



Chemfix Products Ltd MILL STREET EAST WF12 9BQ DEWSBURY UNITED KINGDOM Eurofins Product Testing A/S Smedeskovvej 38 8464 Galten Denmark

CustomerSupport@eurofins.com www.eurofins.com/VOC-testing

VOC TEST REPORT VOC Content

24 June 2021

1 Sample Information

Sample name Chemfix PESF (PESF TOP)

Sample no. 392-2021-00231002

Production date 24/03/2021
Batch No. 1363594
Sample reception 06/05/2021

2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
SCAQMD Rule 1168	Pass	October 2017
LEED v4.1 (VOC Content)	Pass	February 2021

Full details based on the testing and direct comparison with limit values are available in the following pages Regarding pass/fail decision rule please see appendix

Pernille Krintel
Analytical Service Manager

Janne Rothmann Norup Analytical Service Manager



3 Applied Test Methods

3.1 General Test References

Regulation, protocol or standard	Scope	Version
SCAQMD Rule 1168	Adhesive and sealant applications	October 2017

3.2 Specific Laboratory Sampling and Analyses

Test	Regulation, protocol or standard	Version	Internal SOP	Limit of detection	Uncertainty Um¤
				[g/L]	%
Solids Content	ASTM D2369	2020	71 M 544830	1	10
VOC	ASTM D2369	2020	71 M 544830	1	10

3.3 Preparation of the Test Specimen

The sample was homogenised and left to cure for 1 hour before applying a portion of the sample to the test dish.

4 Results

4.1 VOC content

	Remarks on the test results	Results	Unit
Density *	Tested by the lab	1.72	g/mL
Water Content 1	Tested by the lab	0.10	% (w/w)
Exempt compounds *	Assumed to be 0	0	% (w/w)
Solids Content	Tested by the lab	91	% (w/w)
VOC content (less water)	Calculated based on the results above	160	g/L

4.2 Comparison with Limit Values of VOC Content (less Water)

Parameter	Results	Product type	Regulation or protocol	VOC limit
	[g/L]			[g/L]
VOC content	160	Other adhesive	SCAQMD Rule 1168	250





5 Appendices

5.1 How to Understand the Results

5.1.1 Acronyms Used in the Report

- < Means less than
- > Means bigger than
- * Not a part of our accreditation
- Please see section regarding uncertainty in the Appendices
- 1 Analysed by another Eurofins laboratory

5.2 Description of VOC Content Test

5.2.1 Testing of VOC

Volatile content of the sample was determined gravimetrically by heating to 110 °C in 60 minutes. Multicomponent products are mixed according to the manufacturer's instructions and allowed to cure before heating.

The result is the average of two replicates. The result was calculated as:

$$VOC = \frac{([g\ All\ Volatiles] - [g\ Water] - [g\ Exempt\ Compounds])}{([liter\ Material] - [liter\ Water] - [liter\ Exempt\ Compounds])}$$

5.2.2 Testing of Density

The density was calculated using gravimetric and volumetric determination. The result is the average of three determinations.

5.2.3 Testing of Water Content

The water content was determined using a Karl-Fischer titration.

5.3 Uncertainty of the Test Method

Um(%): The expanded uncertainty Um is equal to 2 x RSD%.





5.4 Decision Rules

Eurofins Product Testing A/S, declare statement of conformity based on the "Binary Statement for Simple Acceptance Rule" described in ILAC's "Guidelines on decision Rules and Statements of Conformity" ILAC-G8:09/2019.

This means that results above the detection limit are always reported with two significant digits. Results are evaluated with the same number of significant digits as the corresponding limit values, and conformity is based on results being less than or equal to limit values.

For limit values with more than two significant digits, the third digit will be used to confirm whether a result is below or equal to the limit value. It will always be indicated in the evaluation table if this expanded evaluation is performed.

For further information please visit www.eurofins.dk/product-testing/om-os/beslutningsregler/

5.5 Version History

Report date	Report number	Modification
24/06/2021	392-2021-00231002_XG_EN	Current version