



Bit United Ltd  
 London Road 5  
 SW17 9JR  
 United Kingdom

Eurofins Product Testing A/S  
 Smedeskovvej 38  
 DK-8464 Galten  
 Denmark

Tel. +45 70 22 42 76  
 Fax +45 70 22 42 75  
 ProductTesting-GA@eurofins.com  
 www.eurofins.com/product-emissions

Date  
 13 August 2014  
 Our ref.  
 392-2014-00095702B

## Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

### Sample material

Sample identification	BIT PESF / EASF / VESF / NORD / TROPIC
Product type	Multipurpose construction adhesives
Product data, according to manufacturer	Density: 1.61 g/ml at 20 °C ** Water content: 0 g/l** Exempt compounds: none ***
Date received	28 May 2014
Analytical period	30 May 2014 – 10 June 2014

### Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty, U <sub>m</sub> (%)
LEED 2009 EQ c4.1 (Modified)	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

20 cm sample was dispensed and discarded. Further sample was dispensed in a preweighed dish and allowed to sit for 1 hour (durometer reading > 80). Volatile content of the sample was determined gravimetrically by heating up to 110 °C for 60 minutes. The result is the average of double testing. The result is calculated as:

$$([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$$

U<sub>m</sub> (%): The expanded uncertainty U<sub>m</sub> is equal to 2 x RSD%, see also [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty).

### Analytical results

Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
99.6 %	0 % **	0 %***	6.8	70 *

\* VOC limit for "Multipurpose construction adhesives"

\*\* Given by the client

\*\*\* No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Søren Ryom Villadsen  
 Contact Person

Morten Sielemann  
 Analytical Chemist