

Clinker 32.5 N

Standard specification	Result	specifics
chemical composition		
	23.01%	SiO ₂
	5.23%	Al ₂ O ₃
	4.23%	Fe ₂ O ₃
	63.27%	CaO
	0.96%	MgO
	0.82%	SO ₃
	0.45%	K ₂ O
	0.17%	Na ₂ O
< 0.10	0.01%	CL
	0.24%	Loss on ignition
	35.20%	C ₃ S
	40.10%	C ₂ S
	6.73%	C ₃ A
	12.85%	C ₄ AF
	1.09%	Free Lime
< 2.0	1.78 ppm	Cr+6