

Clinker 42.5 N

Standard specification	Result	specifics
chemical composition		
	22.02%	SiO ₂
	5.30%	Al ₂ O ₃
	3.84%	Fe ₂ O ₃
	64.48%	CaO
	1.16%	MgO
	0.75%	SO ₃
	0.52%	K ₂ O
	0.29%	Na ₂ O
< 0.10	0.01%	CL
	0.20%	Loss on ignition
	49.03%	C ₃ S
	26.43%	C ₂ S
	7.52%	C ₃ A
	11.68%	C ₄ AF
	0.43%	Free Lime
< 2.0	1.95 ppm	Cr+6