

Fabripatch® H

- Cement-Based
- Polymer Modified
- Excellent Strength
- High Chemical Resistance
- Versatile Applications

DESCRIPTION AND USE

FABRIPATCH® H is a cement-based, acrylic-modified, versatile patching, repairing, levelling, and re-surfacing material designed to bond to a variety of cementitious and masonry substrates. While FABRIPATCH® H is primarily intended for use on horizontal surfaces, vertical applications are also possible. The product is ideally suited for use on ramps, stairs, walkways and concrete floors.

ADVANTAGES

The specially formulated polymer additive employed with FABRIPATCH® H not only imparts excellent compressive, tensile, flexural, and bond strengths, it also gives the product very high chemical resistance.

APPLICATION

Surfaces to be coated with FABRIPATCH® H must be clean and sound. All oil, grease, laitance, dirt and residual chemicals should be removed prior to application. Any loose or disintegrated material should be chipped away before beginning installation. Slightly dampen surfaces to be treated. Place a portion of the FABRIPATCH® H powder in a clean container and add sufficient FABRIPATCH® LIQUID RESIN to create a slurry mix. Brush this slurry mix on the surface to be patched. Add additional powder to the remainder of the slurry mix until a stiff mortar consistency is obtained. Trowel this mix into place. For patches deeper than 2 inches add 20 - 25 lbs of clean pea gravel per 50 lb pail of FABRIPATCH® H.

Care should be taken to avoid over trowelling as this could lead to separation.

CAUTION

FABRIPATCH® H is highly alkaline and is therefore irritating to eyes and skin. In case of contact, thoroughly flush with large amounts of water and call physician immediately. DO NOT RUB EYES. Wash thoroughly after handling. Do not take internally. Keep out of reach of children. Keep product dry. Consult Material Safety Data Sheet before using this product.

LIMITATIONS

On re-surfacing projects, adequate allowance must be made for control and movement joints.

FABRIPATCH®H should not be applied in thicknesses greater than 1 inch without layering (scarifying the surface between layers).

FABRIPATCH®H must not be retempered nor be surface wetted to aid in trowelling.

Bulletin 62-B
08/'03

COVERAGE

The following chart shows approximate coverages for a 50 lb pail of FABRIPATCH®H.

THICKNESS	COVERAGE
¼ inch	23.5 sq.ft.
½ inch	11.8 sq.ft.
¾ inch	7.9 sq.ft.
1 inch	5.9 sq.ft.

GUARANTEE

FABRIKEM MANUFACTURING LTD. guarantees its products when applied in accordance with its printed instructions. Results of inadequate surface preparation, improper mixing, incorrect application, inadequate protection, and other factors beyond the manufacturer's control cannot be held to the manufacturer's responsibility. No responsibility can be accepted beyond the purchase price of the product.

Bulletin 62-B — 08/03

www.fabrikem.com

20361 DUNCAN WAY, LANGLEY, BC CANADA V3A 7N3
T 604-532-3883 F 604-532-3164 E info@fabrikem.com


FABRIKEM
Toll Free: 800-441-7456