

SP0150849
FINAL REPORT

Multi Element Package



AMERICAN ASSAY LABORATORIES
1500 GLENDALE AVE.
SPARKS, NV USA 89431-5902
Ph.(775) 356-0606
Fax.(775) 356-1413
EMAIL: info@aallabs.com

Xtra Energy Corp

COPIES TO : Steven Cyros
scyros@mrewholesalers.com

CLIENT REFERENCE No: KS24 04-20

RECEIVED : 14-Jun-2024

No. SAMPLES : 24

REPORTED : 14-Aug-2024

MAIN SAMPLE TYPE : ROCK

All Laboratory Analysis were preformed between the above Received and Reported dates

COMPANY DISCLAIMER :-
When small samples are submitted, AAL may process the sample at smaller then specified weights to retain some pulp for quality control reassay. When Values exceed upper limits, AAL will run an Over Range analysis, to establish an accurate value. Additional cost will apply. Due to USDA Soil Quarantine programs - all foreign and some domestic soil material must be decontaminated by drying @ 125c for 48 hours, which will result in loss of Mercury (Hg).

NEVADA LEGISLATIVE DISCLAIMER :-
The results of this assay were based solely upon the content of the sample submitted. Any decision to invest should be made only after the potential investment value of the claim or deposit has been determined based on the results of assays of multiple samples of geological materials collected by the prospective investor or by a qualified person selected by him and based on an evaluation of all engineering data which is available concerning any proposed project. Nevada State Law NRS 519.130.

ANALYSIS	Wt	Au	Pd	Pt	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga	Ge	Hf	Hg	In	K	La	Li
METHOD	P-C7J3	'APGM30	'APGM30	'APGM30	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52
UNIT	g	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
LOWER LIMIT	0.01	0.003	0.003	0.005	0.3	100	0.5	2	0.01	0.01	100	0.02	0.2	0.2	0.2	0.2	0.5	300	0.05	0.02	0.03	0.01	0.008	300	0.1	2

ANALYSIS	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U	V	W	Y	Zn
METHOD	IM-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52	I-4AB52
UNIT	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
LOWER LIMIT	100	5	0.2	100	0.03	0.5	20	3	0.8	0.003	30	0.05	0.05	0.05	0.05	5	0.03	0.03	0.08	30	0.008	0.05	3	0.07	0.05	3

ANALYSIS	Zr	Ir	Pd	Pt	Rh	Ru
METHOD	IM-4AB52	IM-NF5	IM-NF5	IM-NF5	IM-NF5	IM-NF5
UNIT	ppm	ppm	ppm	ppm	ppm	ppm
LOWER LIMIT	0.3	0.001	0.001	0.001	0.001	0.001

SIGNATORY ANALYSIS

SP0150849
FINAL REPORT



AMERICAN ASSAY LABORATORIES
1500 GLENDALE AVE.
SPARKS, NV USA 89431-5902
Ph. (775) 356-0606
Fax. (775) 356-1413
EMAIL: AALLABS@NVBELL.NET

	Abbreviation	Definition
Preparation	DIP	Sample Destroyed in Preparation
	DIS	Sample Destroyed in Shipment
	ISS	Insufficient Sample Submitted
	SDI	Sample Diesel Impregnated
	SHI	Sample Hydraulic Impregnated
	SNR	Sample Not Received
Analysis	STD - ??	International Reference Material Standard
	STD - AAL##	AAL generated standard material
	BLANK	AAL Laboratory Silica Blank
	DTF	Data to Follow
	DL	Detection Limit of Method
	< or -	Less Than Lower Detection Limit of Method
	>	Greater than Upper Limit of Method
	N/A	Not Analyzed
	NR	Not Reported
	(R) column	Laboratory repeat weigh, digestion, analysis from original pulp or reject resplit
	D or -D after Sample ID	Client submitted duplicate rig split sample
	-R after Sample ID	Repeat analysis from original pulp reweigh, digestion and analysis
	-X after Sample ID	Repeat analysis from reject resplit, preparation, weigh, digestion and analysis
	ppb	Parts per Billion 0.001 ppm = 1 ppb
	ppm	Parts per Million 1 ppm = 1 mg/Kg
	OPT	Troy Ounces per Short Ton (2,000 lbs) (1 ppm = 0.02917 OPT)
	Oz	Troy Ounce = 31.103 grams
	%	Percent 1%=10,000 ppm
	g	Grams 1g=0.001 kilogram
	mg	Milligrams 1mg=0.001grams
	Kg	Kilograms 1Kg=1000grams
	lbs	Pounds 1lb=0.454kilogram
Method	FA-PB##	Fire Assay Lead Collection - ## sample weight in grams
	GRAV	Gravimetric (Weighed) finish
	SF	Screen Fire Assay reporting a plus, 2 minus fractions and a head Calc
	+ ###	Plus Fraction (Retained on top of Mesh) ###Screen Size
	- ###	Minus Fraction (Passed through Mesh) ###Screen Size
	CN	Cyanide Extraction
	ORE GRADE	2g sample made to 1000ml volumetric for results > upper limit of method
	Ox-H2SO4 or -HCl	Dilute acid leach for oxide fraction in copper or molybdenum analysis
	QLA	Dilute 10%H2SO4/0.5%Fe2(SO4)3 30C leach for acid soluble copper
	QLT	Dilute 15%H2SO4 30C leach for acid soluble copper
	SAP	Dilute 5%H2SO4/0.5%Fe2(SO4)3 85C leach for acid soluble & chalcocite copper
	D#A	Digestion #=2,3 or 4 Acids
		2A=HCl/HNO3 3A=HCl/HNO3/HClO4 4A=HCl/HNO3/HF/HClO4
	HCl	Hydrochloric Acid(37%w/v) Boiling Point 109C
	HF	Hydrofluoric Acid(48%w/v) Boiling Point 108C Extreme Health Hazard
	HClO4	Perchloric Acid(69%w/v) Boiling Point 203C Extreme Fire/Explosion Hazard
	HNO3	Nitric Acid(69%w/v) Boiling Point 121C
	H2SO4	Sulfuric Acid(98% w/v) Boiling Point 338C
	ICP-xB or -xZ	ICP-AES and/or ICP-MS analysis using x=2, 3 or 4 acid digestion
	LiBO2-C	Lithium Metaborate fusion in Carbon crucible
	Na2O2-C	Sodium Peroxide fusion in Carbon crucible
	Na2O2-Zr	Sodium Peroxide fusion in Zirconium crucible
Technique	AAS	Atomic Absorption Spectroscopy
	ICP-AES	Inductively Coupled Plasma Atomic Emission Spectroscopy
	ICP-MS	Inductively Coupled Plasma Mass Spectroscopy
	RG	Research Grade (Low detection limit ICP-AES)
	UT	Ultra Trace (ICP-AES+ICP-MS analyses)
	XRF-ED or -WD	X-Ray Fluorescence (-ED = Energy Dispersive) (-WD = Wavelength Dispersive)
	XRD	X-Ray Diffraction
	ELTRA-I	Carbon & Sulfur infrared detection analyzer inductive heating
	ELTRA-R	Carbon, Hydrogen & Sulfur infrared detection analyzer resistance furnace
	LECO-I	Nitrogen & Oxygen infra red detection analyzer inductive heating
	MW	Microwave Digestion (-PT is at 1500psig and 300C)
	SG-WD or -HP	Specific Gravity-WD=Water Displacement -HP=Helium Pycnometer 1g/cm3=62.4lbs/ft3

SP0150849
FINAL REPORT
CLIENT : Xtra Energy Corp
PROJECT : King Solomon Mine
REFERENCE : KS24 04-20
REPORTED : 14-Aug-2024

SAMPLES	Wt	Au	Pd	Pt	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Ce	Co
	P-C7J3	IO-FAPGM30	IO-FAPGM30	IO-FAPGM30	IM-4AB52	IM-4AB52	IM-4AB52	IM-4AB52	IM-4AB52	IM-4AB52	IM-4AB52	IM-4AB52	IM-4AB52	IM-4AB52
	0.01 g	0.003 ppm	0.003 ppm	0.005 ppm	0.3 ppm	100 ppm	0.5 ppm	2 ppm	0.01 ppm	0.01 ppm	100 ppm	0.02 ppm	0.2 ppm	0.2 ppm
KS24-04	361.90	0.016	<0.003	<0.005	0.7	51084	74.3	234	1.50	0.21	66680	0.18	11.1	9.5
KS24-05	368.50	0.021	<0.003	<0.005	0.7	83314	136.8	414	2.57	0.32	35770	0.18	15.8	15.2
KS24-06	350.20	0.016	<0.003	<0.005	0.5	90756	104.5	461	2.95	0.27	24163	0.14	17.9	15.1
KS24-06-X		0.017	<0.003	<0.005	0.5	88042	100.7	453	2.90	0.31	23596	0.13	17.2	14.5
KS24-07	358.50	0.026	<0.003	<0.005	0.8	85559	119.6	454	2.59	0.25	32350	0.16	17.6	15.3
KS24-08	376.60	0.046	<0.003	<0.005	0.9	87118	299.6	520	2.71	0.39	17932	0.09	16.4	16.3
KS24-09	370.00	0.062	<0.003	<0.005	1.6	81940	300.8	383	2.52	0.29	39370	0.41	19.7	16.9
BLANK		<0.003	<0.003	<0.005	<0.3	1691	2.0	4	0.02	<0.01	305	<0.02	3.1	0.6
KS24-10	407.60	0.038	<0.003	<0.005	0.9	92937	155.7	482	2.98	0.21	21853	0.21	17.6	14.6
KS24-11	383.80	0.044	<0.003	<0.005	0.6	75207	325.1	482	2.22	0.27	29459	0.32	17.7	12.9
KS24-11-X		0.044	<0.003	<0.005	0.6	74525	327.3	480	2.20	0.28	29444	0.33	18.1	12.6
KS24-12	647.30	0.722	<0.003	<0.005	4.2	12519	2314.5	95	0.38	0.06	8720	9.56	2.5	3.4
KS24-13	324.90	0.043	<0.003	<0.005	0.5	69941	246.4	314	1.73	0.29	38104	0.82	16.8	8.9
STD - CDN-PGMS-22		1.200	6.390	1.420										
STD - OREAS 906					0.7	74724	26.3	2703	3.02	10.88	5847	0.36	82.7	23.5
KS24-14	436.50	0.054	<0.003	<0.005	<0.3	72213	272.5	474	1.85	0.47	2098	0.57	24.6	1.6
KS24-15	544.00	0.046	<0.003	<0.005	0.7	80893	274.6	455	2.51	0.20	28918	0.13	16.3	10.3
KS24-15-X		0.044	<0.003	<0.005	0.7	81308	275.2	456	2.52	0.18	28926	0.11	17.4	10.5
KS24-16	509.50	0.112	<0.003	<0.005	4.4	72376	501.6	477	2.41	0.29	28323	1.65	18.3	11.1
KS24-17	422.70	0.047	<0.003	<0.005	1.7	80799	261.8	967	5.42	0.46	5884	0.12	33.1	6.9
KS24-18	499.80	0.035	<0.003	<0.005	0.6	75284	413.7	1180	1.94	<0.01	3913	0.62	25.2	0.8
KS24-19	178.20	0.013	<0.003	<0.005	0.9	62908	31.9	301	1.29	0.03	2228	0.05	53.9	1.3
KS24-20	352.20	0.003	<0.003	<0.005	0.5	31968	19.8	206	0.46	0.04	765	<0.02	33.9	2.1
STD - OREAS 682		0.086	0.463	0.871										
STD - OREAS 602b		0.256	1.800	3.880	>100	53594	783.8	>5000	1.67	58.18	6489	4.96	48.0	5.1
STD - OREAS 684														
STD - OREAS 681														

SP0150849
FINAL REPORT
 CLIENT : Xtra Energy Corp
 PROJECT : King Solomon Mine
 REFERENCE : KS24 04-20
 REPORTED : 14-Aug-2024

SAMPLES	Cr IM-4AB52 0.2 ppm	Cs IM-4AB52 0.2 ppm	Cu IM-4AB52 0.5 ppm	Fe IM-4AB52 300 ppm	Ga IM-4AB52 0.05 ppm	Ge IM-4AB52 0.02 ppm	Hf IM-4AB52 0.03 ppm	Hg IM-4AB52 0.01 ppm	In IM-4AB52 0.008 ppm	K IM-4AB52 300 ppm	La IM-4AB52 0.1 ppm	Li IM-4AB52 2 ppm	Mg IM-4AB52 100 ppm	Mn IM-4AB52 5 ppm	Mo IM-4AB52 0.2 ppm
KS24-04	265.9	8.6	37.1	51546	12.87	0.27	0.56	0.04	0.075	14976	6.5	81	24571	1150	1.3
KS24-05	117.5	17.1	20.5	46546	21.10	0.11	0.71	0.05	0.079	24237	8.5	106	18372	684	0.5
KS24-06	142.9	22.2	25.4	47730	22.96	0.09	0.78	0.05	0.071	26752	9.7	70	16863	582	0.6
KS24-06-X	140.4	21.9	22.9	46324	22.67	0.08	0.74	0.05	0.069	26126	9.4	69	16516	573	0.6
KS24-07	115.2	19.1	19.7	43365	22.23	0.12	0.76	0.05	0.075	25163	9.4	66	17465	689	0.4
KS24-08	90.2	18.7	19.2	56535	22.49	0.12	0.73	0.06	0.061	27242	8.9	14	10704	560	0.5
KS24-09	188.1	23.9	18.2	43841	21.52	0.26	0.76	0.09	0.066	22818	10.5	79	16906	778	1.2
BLANK	1.7	0.9	<0.5	<300	1.38	<0.02	0.08	<0.01	<0.008	601	2.2	<2	<100	<5	<0.2
KS24-10	98.6	20.4	32.5	46961	23.20	0.06	0.72	0.08	0.067	27001	9.5	18	15048	541	0.3
KS24-11	251.3	23.1	22.5	36881	19.92	0.06	0.77	0.11	0.043	19792	10.0	80	13492	711	1.4
KS24-11-X	250.7	23.2	23.1	36130	19.37	0.05	0.78	0.12	0.043	19723	10.0	79	13457	708	1.3
KS24-12	461.7	4.7	91.4	13825	3.87	0.06	0.14	1.37	0.009	2503	2.3	42	3664	348	1.2
KS24-13	227.6	12.1	18.7	39901	16.12	0.03	0.79	0.23	0.035	16621	9.1	37	15198	732	0.9
STD - CDN-PGMS-22															
STD - OREAS 906	9.3	6.4	3113.7	55409	27.81	0.27	6.91	0.01	1.212	27816	41.1	20	2874	386	3.7
KS24-14	197.9	6.9	<0.5	7387	18.56	0.04	1.95	0.09	0.056	14132	13.8	205	1305	175	0.9
KS24-15	141.7	15.6	20.8	43471	17.78	<0.02	0.67	0.04	0.039	23839	9.0	22	15670	816	0.6
KS24-15-X	141.4	15.7	21.3	43587	17.50	<0.02	0.69	0.04	0.040	23777	9.7	22	15722	823	0.5
KS24-16	330.6	23.0	35.2	31867	15.61	0.03	0.55	0.91	0.023	18769	10.6	104	6971	801	3.4
KS24-17	166.6	11.7	11.3	28231	16.47	<0.02	1.02	0.10	0.018	26332	18.7	19	3186	762	3.2
KS24-18	253.4	5.8	3.5	8235	16.04	<0.02	1.61	0.02	<0.008	15568	14.1	79	1805	403	0.5
KS24-19	418.7	9.2	4.7	7382	16.37	0.12	1.00	0.33	0.008	20047	27.9	115	1684	41	1.1
KS24-20	769.4	4.6	1.5	7636	8.58	0.09	0.74	1.00	<0.008	10161	17.6	20	928	69	2.2
STD - OREAS 682															
STD - OREAS 602b	34.6	3.7	4903.8	24021	24.17	0.19	4.14	0.46	1.550	17293	25.5	19	767	188	7.4
STD - OREAS 684															
STD - OREAS 681															

SP0150849**FINAL REPORT**

CLIENT : Xtra Energy Corp
PROJECT : King Solomon Mine
REFERENCE : KS24 04-20
REPORTED : 14-Aug-2024

SAMPLES	Na IM-4AB52 100 ppm	Nb IM-4AB52 0.03 ppm	Ni IM-4AB52 0.5 ppm	P IM-4AB52 20 ppm	Pb IM-4AB52 3 ppm	Rb IM-4AB52 0.8 ppm	Re IM-4AB52 0.003 ppm	S IM-4AB52 30 ppm	Sb IM-4AB52 0.05 ppm	Sc IM-4AB52 0.05 ppm	Se IM-4AB52 0.05 ppm	Sn IM-4AB52 0.05 ppm	Sr IM-4AB52 5 ppm	Ta IM-4AB52 0.03 ppm	Te IM-4AB52 0.03 ppm
KS24-04	2687	1.93	22.0	430	55	71.2	<0.003	4762	10168.00	10.05	2.47	1.36	495	0.12	0.08
KS24-05	4065	2.44	32.4	570	18	140.4	0.003	4907	171.90	15.17	0.43	2.25	329	0.18	0.08
KS24-06	4441	2.30	31.8	614	22	156.5	<0.003	3783	1930.89	16.34	2.47	2.34	262	0.15	0.05
KS24-06-X	4316	2.28	31.2	608	22	149.5	<0.003	3672	1890.52	16.04	1.50	2.29	257	0.14	0.06
KS24-07	4205	2.13	31.3	592	23	138.3	<0.003	2888	1335.34	15.80	2.14	2.33	350	0.14	0.05
KS24-08	4173	2.41	31.3	605	14	152.3	<0.003	2988	159.61	15.07	3.88	2.27	242	0.16	0.05
KS24-09	3402	2.24	34.0	604	24	129.2	<0.003	6171	671.03	14.76	3.12	2.15	331	0.14	0.04
BLANK	<100	0.25	1.8	<20	6	2.1	<0.003	<30	<0.05	0.25	1.42	0.09	15	0.03	<0.03
KS24-10	5332	2.01	31.9	623	25	155.1	<0.003	4092	1848.22	16.77	2.25	2.27	260	0.13	0.04
KS24-11	4185	2.35	28.9	480	24	109.0	<0.003	5179	2749.09	11.51	2.51	1.83	397	0.14	0.04
KS24-11-X	4163	2.36	28.3	486	25	109.7	<0.003	5232	2746.09	11.47	1.10	1.83	392	0.14	0.04
KS24-12	353	1.15	11.2	141	482	13.1	<0.003	94796	309080.00	2.03	2.09	0.82	111	0.04	0.43
KS24-13	14926	2.04	20.6	514	48	90.1	<0.003	7225	2179.40	10.55	3.32	1.35	389	0.12	0.06
STD - CDN-PGMS-22															
STD - OREAS 906	25480	14.83	5.1	276	33	138.8	<0.003	372	24.44	4.80	5.05	4.05	180	1.02	0.12
KS24-14	27985	5.44	3.8	93	7	74.0	<0.003	3344	243.07	1.36	2.63	1.30	111	0.35	<0.03
KS24-15	4150	1.90	19.9	588	30	133.4	<0.003	6612	5269.04	14.31	1.38	1.64	244	0.12	0.04
KS24-15-X	4168	1.91	20.1	597	30	134.1	<0.003	6664	5254.43	14.35	2.52	1.64	246	0.11	0.05
KS24-16	2497	1.76	23.1	437	162	106.1	<0.003	31372	47898.00	10.79	1.94	1.61	258	0.10	0.09
KS24-17	12144	3.55	14.5	465	64	152.2	<0.003	421	1051.09	9.23	1.96	1.54	140	0.24	<0.03
KS24-18	25592	4.82	3.8	84	11	91.5	<0.003	1630	944.55	1.26	3.27	1.30	102	0.32	<0.03
KS24-19	1567	4.76	9.4	96	91	114.2	<0.003	4940	353.56	6.04	1.50	1.71	82	0.30	<0.03
KS24-20	1234	4.98	10.0	50	14	47.8	<0.003	3682	194.53	2.52	0.34	1.04	49	0.28	<0.03
STD - OREAS 682															
STD - OREAS 602b	13471	14.09	12.8	246	402	60.3	0.008	21646	102.09	3.48	21.74	8.56	270	1.02	34.09
STD - OREAS 684															
STD - OREAS 681															

SP0150849**FINAL REPORT**

CLIENT : Xtra Energy Corp
PROJECT : King Solomon Mine
REFERENCE : KS24 04-20
REPORTED : 14-Aug-2024

SAMPLES	Th	Ti	Tl	U	V	W	Y	Zn	Zr	Ir	Pd	Pt	Rh	Ru
	IM-4AB52 0.08 ppm	IM-4AB52 30 ppm	IM-4AB52 0.008 ppm	IM-4AB52 0.05 ppm	IM-4AB52 3 ppm	IM-4AB52 0.07 ppm	IM-4AB52 0.05 ppm	IM-4AB52 3 ppm	IM-4AB52 0.3 ppm	IM-NF5 0.001 ppm	IM-NF5 0.001 ppm	IM-NF5 0.001 ppm	IM-NF5 0.001 ppm	IM-NF5 0.001 ppm
KS24-04	<0.08	394	0.485	0.65	66	0.50	10.98	61	16.1	0.035	<0.001	<0.001	<0.001	0.020
KS24-05	<0.08	669	0.840	0.85	108	1.58	9.92	83	19.7	0.023	<0.001	<0.001	<0.001	<0.001
KS24-06	<0.08	644	0.930	0.91	123	0.88	9.09	91	21.4	0.029	<0.001	<0.001	0.001	<0.001
KS24-06-X	<0.08	635	0.920	0.89	121	0.86	8.77	87	20.8	0.085	<0.001	<0.001	<0.001	0.007
KS24-07	<0.08	600	0.873	0.90	109	1.22	9.71	77	21.1	0.073	<0.001	<0.001	<0.001	<0.001
KS24-08	<0.08	704	0.925	0.95	108	1.42	8.54	72	20.4	0.039	<0.001	<0.001	<0.001	<0.001
KS24-09	<0.08	597	0.869	0.95	135	1.55	11.04	131	21.5	0.031	<0.001	<0.001	<0.001	0.009
BLANK	<0.08	81	0.017	0.17	<3	0.08	0.89	4	2.2	0.043	<0.001	<0.001	<0.001	<0.001
KS24-10	<0.08	594	0.905	0.84	122	0.99	7.92	102	19.3	0.032	<0.001	<0.001	<0.001	<0.001
KS24-11	<0.08	451	0.722	0.85	82	1.24	8.52	133	19.4	0.046	<0.001	<0.001	<0.001	<0.001
KS24-11-X	<0.08	442	0.708	0.86	81	1.28	8.43	128	19.6	0.075	<0.001	<0.001	0.005	0.002
KS24-12	<0.08	174	1.136	0.16	10	0.60	2.15	2206	3.8	0.038	<0.001	<0.001	<0.001	0.025
KS24-13	<0.08	423	0.546	0.86	65	0.90	9.99	270	19.9	0.145	<0.001	<0.001	<0.001	0.002
STD - CDN-PGMS-22										0.047	6.122	1.290	0.004	0.069
STD - OREAS 906	0.14	1100	0.670	4.96	6	2.06	14.39	148	245.1					
KS24-14	<0.08	349	0.452	1.84	5	1.14	4.53	209	45.6	0.049	<0.001	<0.001	<0.001	0.002
KS24-15	<0.08	550	0.700	0.78	100	0.97	7.67	89	18.3	0.019	<0.001	<0.001	<0.001	0.010
KS24-15-X	<0.08	588	0.736	0.78	100	1.04	7.91	84	19.0	0.043	<0.001	<0.001	0.044	0.006
KS24-16	<0.08	415	0.734	0.70	110	1.08	6.76	534	14.4	0.024	<0.001	<0.001	0.018	0.008
KS24-17	<0.08	977	0.762	1.21	75	4.43	7.09	110	24.1	0.055	<0.001	<0.001	0.004	0.003
KS24-18	<0.08	367	0.429	1.51	5	1.21	3.86	195	32.4	0.047	<0.001	<0.001	<0.001	<0.001
KS24-19	<0.08	1320	0.750	1.17	63	2.83	5.93	26	26.9	0.050	<0.001	<0.001	<0.001	0.003
KS24-20	<0.08	1224	0.490	0.76	28	1.39	3.87	8	19.4	0.043	<0.001	<0.001	<0.001	0.002
STD - OREAS 682										0.022	0.373	0.961	0.062	0.070
STD - OREAS 602b	34.05	1365	2.094	3.89	15	13.16	8.63	867	147.1					
STD - OREAS 684										0.102	1.812	3.883	0.325	0.467
STD - OREAS 681														