

UltraLite Beehive Kiln ©

Firing PMC or Art Clay

3/18/2018

The UltraLite Beehive Kiln is the perfect choice for firing Metal Clay pieces. The kiln heats quickly and evenly and you cannot over-fire using this method. Metal clay pieces should be completely dry before firing. If desired, place one ceramic disk on the top of the kiln cover while the kiln is on. This provides a heated surface that will help your pieces dry quickly and thoroughly (Dries pieces in approximately 10 Minutes). Be sure to remove the insert from the top prior to firing

Firing Procedure:

- Place the round ceramic insert over the heating element.
- Cover the kiln and preheat for 35 minutes.
- Remove the cover.
- Place the dried Metal Clay on the heated insert
- Do not cover during firing.
- The piece should glow orange red (Salmon color).
- Fire 30 minutes
- After firing, cover the kiln to reheat for 15 minutes before firing more pieces.

Please note: Some slight smoking and/or a small flame may occur and is normal.

For other brand of Metal Clays and more firing options use the Temperature Controller.

UltraLite Beehive Kiln ©

Firing PMC or Art Clay

3/18/2018

The UltraLite Beehive Kiln is the perfect choice for firing Metal Clay pieces. The kiln heats quickly and evenly and you cannot over-fire using this method. Metal clay pieces should be completely dry before firing. If desired, place one ceramic disk on the top of the kiln cover while the kiln is on. This provides a heated surface that will help your pieces dry quickly and thoroughly (Dries pieces in approximately 10 Minutes). Be sure to remove the insert from the top prior to firing

Firing Procedure:

- Place the round ceramic insert over the heating element.
- Cover the kiln and preheat for 35 minutes.
- Remove the cover.
- Place the dried Metal Clay on the heated insert
- Do not cover during firing.
- The piece should glow orange red (Salmon color).
- Fire 30 minutes
- After firing, cover the kiln to reheat for 15 minutes before firing more pieces.

Please note: Some slight smoking and/or a small flame may occur and is normal.

For other brand of Metal Clays and more firing options use the Temperature Controller.