

Daewoo Grease Complex EP 2 - 3

Meets and exceeds: for EP2: ISO 6743-9: L-XBEHB 2; DIN 51502: KP2P-20 for EP3: ISO 6743-9: L-XBDHB 3; DIN 51502: P3N-20

TYPICAL PROPERTIES

Soap/Thickener

Lithium Complex

NLGI Grade	ASTM D217	2	3
Color	Visual	Red	Red
Appearance	Visual	Smooth	Smooth
Operating Temperature range, °C	-	-25 to 160	-25 to 160
Penetration @ 25°C, 0.1 mm	ASTM D217	265 - 295	220 - 250
Dropping point, °C	IP 396/DIN ISO 2176	≥275	≥240
Kinematic viscosity of the base oil @ 40°C, mm ² /s	ASTM D445	165	165

AVAILABLE PACKS

0.5 KG, 1 KG, 3 KG, 15 KG, 175 KG



Daewoo Grease EP 2 - 3

Meets and exceeds: for EP2: ISO 6743-9: L-XBEHB 2; DIN 51502: KP2P-20 for EP3: ISO 6743-9: L-XBDHB 3; DIN 51502: P3N-20

TYPICAL PROPERTIES

Soap/Thickener

Lithium

NLGI Grade	ASTM D217	2	3
Color	Visual	Glazy Yellow	Glazy Yellow
Appearance	Visual	Smooth	Smooth
Operating Temperature range, °C	-	-25 to 140	-25 to 140
Penetration @ 25°C, 0.1 mm	ASTM D217	265 - 295	220 - 250
Dropping point, °C	IP 396/DIN ISO 2176	≥190	≥190
Kinematic viscosity of the base oil @ 40°C, mm ² /s	ASTM D445	165	165

AVAILABLE PACKS

0.5 KG, 1 KG, 3 KG, 15 KG, 175 KG



Daewoo Grease MP 2 - 3

Meets and exceeds: for MP2: ISO 6743-9: L-XBCEA 2; DIN 51502: K2K-25 for MP3: ISO 6743-9: L-XBCEA 3; DIN 51502: K3K-20

TYPICAL PROPERTIES

Soap/Thickener

Lithium

NLGI Grade	ASTM D217	2	3
Color	Visual	Glazy Yellow	Glazy Yellow
Appearance	Visual	Smooth	Smooth
Operating Temperature range, °C	-	-25 to 120	-25 to 120
Penetration @ 25°C, 0.1 mm	ASTM D217	265 - 295	220 - 250
Dropping point, °C	IP 396/DIN ISO 2176	≥185	≥185
Kinematic viscosity of the base oil @ 40°C, mm ² /s	ASTM D445	150	150

AVAILABLE PACKS

0.5 KG, 1 KG, 3 KG, 15 KG, 175 KG



Daewoo Grease MP 0 - 1

Meets and exceeds: for MP0: ISO 6743-9: L-XBCEB 0; DIN 51502: MP0K-25 for MP1: ISO 6743-9: L-XBCEB 1; DIN 51502: KP1K -30

TYPICAL PROPERTIES

Soap/Thickener

Lithium

NLGI Grade	ASTM D217	0	1
Color	Visual	Glazy Yellow	Glazy Yellow
Appearance	Visual	Smooth	Smooth
Operating Temperature range, °C	-	-25 to 100	-25 to 100
Penetration @ 25°C, 0.1 mm	ASTM D217	370	325
Dropping point, °C	IP 396/DIN ISO 2176	160	175
Kinematic viscosity of the base oil @ 40°C, mm ² /s	ASTM D445	220	220

AVAILABLE PACKS

0.5 KG, 1 KG, 3 KG, 15 KG, 175 KG

