


TRUMETAL PVDF CUSTOM COLOR OFFERINGS



Regal White
SR .85 SRI 83



Snow White
SR .75 SRI 73



Almond
SR .64 SRI 60



Sandstone
SR .53 SRI 52



Surrey Beige
SR .38 SRI 38



Brownstone
SR .40 SRI 40




Mansard Brown
SR .28 SRI 28



Ash Gray
SR .34 SRI 34




Tundra
SR .35 SRI 35



Slate Gray
SR .15 SRI 15



Charcoal Gray
SR .33 SRI 33




Medium Bronze
SR .30 SRI 27



Aged Bronze
SR .28 SRI 27



Dark Bronze
SR .24 SRI 23



Matte Black
SR .25 SRI 25



Regal Red
SR .49 SRI 48



Colonial Red
SR .35 SRI 29



Brandywine
SR .27 SRI 25



Patina Green
SR .44 SRI 43



Hemlock Green
SR .34 SRI 33



Teal Green
SR .30 SRI 29



Evergreen
SR .24 SRI 22



Hartford Green
SR .27 SRI 26



Roman Blue
SR .25 SRI 25



Regal Blue
SR .25 SRI 24



Silver
SR .57 SRI 56



Pre-Weathered GALVALUME®
SR .27 SRI 24



Champagne
SR .37 SRI 37



Copper Metallic
SR .51 SRI 58

> Final color selection should be made from actual color chips.

> For the most current information, visit unitedsteelsupply.com.

> A 35-year limited paint warranty is available for all colors upon written request. Please inquire. (Outside the continental United States, please inquire).

> Solar Reflectivity (SR): Solar reflectivity or reflectance is the measure of a material's ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a value of 1.0 indicates total reflectance.

> Solar Reflectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing. For more information, visit usgbc.org.