



## Technical Information and Typical Properties

### MBI One Side-Cling Machine Film with UVI .90 mil

---

#### Product Description

MBI is Sigmas ultra-premium, one-sided cling cast film with UVI additive designed for high speed/high volume applications where outdoor storage is a critical component of the application. MBI is a true one-sided cling film allowing pallets to touch during storage without any damages to the the package when seperated.

---

#### General

Applications                      • High Volume                      • High speed wrapping                      • One-side cling required  
Revision Date                      6/22/2015                      Available in 20 and 30 inch widths

Film Properties	Typical Value		Test Method
	(English)	Tolerance	
Tensile Strength at Yield MD	1275 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1175 psi	± 15%	ASTM D882
Tensile Strength at Break MD	6600psi	± 15%	ASTM D882
Tensile Strength at Break TD	3900psi	± 15%	ASTM D882
Elongation at Break MD	505%	± 15%	ASTM D882
Elongation at Break TD	635%	± 15%	ASTM D882
Protrusion Puncture	12.6 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	29.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	295 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	595 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

---

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	24.1 micron	

---

Manufactured in Canada by  
**Sigma Stretch Film of Canada**  
 219 Jamieson Bone Rd Belleville Ontario K8N-5A5  
 Phone: 866-848-4400 • 613-966-2781  
 Email: stretch.info@sigmaplastics.com  
 Visit our website at [www.sigmastretchfilm.com](http://www.sigmastretchfilm.com)  
 ©Copyright 2018 Sigma Stretch Film