

Technical Information and Typical Properties

MEV One Side-Cling Cast Machine Film

0.80 mil



Product Description

Evolve is a brand new formulation, made with proprietary resin blends on state of the art extrusion equipment. This all purpose film is a highly engineered, one side cling, cast super film. It's the first of it's kind in North America. Evolve is manufactured on equipment that produces perfect roll edges and tight gauge tolerances, making it perfect for today's high speed wrapping equipment.

General

Applications • High volume • High speed wrapping • One side-cling required Available in 500 and 750 mm widths

| | Typical Value | | |
|----------------------------------|---------------|-----------|-------------|
| Film Properties | (English) | Tolerance | Test Method |
| Tensile Strength at Yield MD | N/A | N/A | N/A |
| Tensile Strength at Yield TD | 2300 psi | ± 15% | ASTM D882 |
| Tensile Strength at Break MD | 3700 psi | ± 15% | ASTM D882 |
| Tensile Strength at Break TD | 6000 psi | ± 15% | ASTM D882 |
| Elongation at Break MD | 525% | ± 15% | ASTM D882 |
| Elongation at Break TD | 650% | ± 15% | ASTM D882 |
| Protrusion Puncture | 6.0 lbs | ± 15% | ASTM D5748 |
| Protrusion Puncture Energy | 16 in-lb | ± 15% | ASTM D5748 |
| Elmendorf Tear Strength MD | 650 g/mil | ± 15% | ASTM D1922 |
| Elmendorf Tear Strength TD | 970 g/mil | ± 15% | ASTM D1922 |
| Cling - Outside to Inside @ 225% | min 150 g/in | ± 15% | ASTM D5458 |

| Dimensions | Value | Tolerance | |
|----------------|-------------|-----------|--|
| Core ID | 3.05 inches | ± 0.05 in | |
| Film Thickness | 20.3 micron | | |

Manufactured with pride in the USA and Canada by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8
Phone: 800-672-9727 • 201-507-9100
Email: stretch.info@sigmaplastics.com
Visit our website at www.sigmastretchfilm.com
©Copyright 2018 Sigma Stretch Film