



Technical Information and Typical Properties

MIT One Sided Cling Machine Film .90 mil



Product Description

Sigma Summit is Sigma's ultra-performance one-side cling, cast film. Summit sets the industry standard with this high quality, consistent machine film perfectly suited for high speed wrapper applications. Summit, in conjunction with our Rite-Gauging methodology will get more product to its destination in as-made condition.

General

Applications: High Volume, High speed wrapping, One-sided cling required
 Revision Date: 6/22/2015 Available in 20 and 30 inch widths

Film Properties	Typical Value (English)	Tolerance	Test Method
Tensile Strength at Yield MD	1300 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1200psi	± 15%	ASTM D882
Tensile Strength at Break MD	6600psi	± 15%	ASTM D882
Tensile Strength at Break TD	3900psi	± 15%	ASTM D882
Elongation at Break MD	520%	± 15%	ASTM D882
Elongation at Break TD	650%	± 15%	ASTM D882
Protrusion Puncture	13 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	27.6 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	300 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	600 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	22.9 micron	

Manufactured with pride in the USA and Canada by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: stretch.info@sigmaplastics.com

Visit our website at www.sigmastretchfilm.com

©Copyright 2018 Sigma Stretch Film