



Material and Performance Specification

ECSC-2 Double Net Straw/Coconut Rolled Erosion Control Product

Description: The ECSC-2 is made with uniformly distributed 70% agricultural straw, 30% coconut fiber and two polypropylene nets securely sewn together with degradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECSC-2 has functional longevity of approximately 24 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 to 1:1 and low to medium flow channels. The ECSC-2 meets Type 3.B specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Materials:	Netting	Matrix	Thread
	<i>Top</i>		
	Mediumweight Photodegradable Polypropylene 0.75" x 0.75" Opening	70% Agricultural Straw 0.385 lbs yd ² 208.9 g/m ²	Degradable 1.50" stitch spacing
	<i>Bottom</i>		
	Lightweight Photodegradable Polypropylene 0.50" x 0.50" Opening	30% Coconut Fiber 0.165 lbs yd ² 89.5 g/m ²	

Roll Sizes:		Standard	Mega
	Width:	7.5 ft (2.3 m)	15.0 ft (4.6 m)
	Length:	120.0 ft (36.6 m)	120.0 ft (36.6 m)
	Weight ±10%:	60.0 lbs (27.2 kg)	120.0 lbs (54.4 kg)
	Area:	100 yd ² (83.6 m ²)	200 yd ² (167.2 m ²)
	#/Pallet:	16	16

Index Value Properties*:

Property	Test Method	Typical
Mass/Unit Area	ASTM D6475	9.45 oz/yd ² (320.4 g/m ²)
Thickness	ASTM D6525	.40 in (10.2 mm)
Tensile Strength-MD	ASTM D6818	178 lb/ft (2.6 kN/m)
Elongation-MD	ASTM D6818	31.3 %
Tensile Strength-TD	ASTM D6818	148 lb/ft (2.2 kN/m)
Elongation-TD	ASTM D6818	22.4 %
Light Penetration	ASTM D6567	13 %
Water Absorption	ASTM D1117	339 %
* May differ depending upon raw material variations		

Bench-Scale Testing* (NTEP*):**

Test Method	Parameters	Results
ECTC Method 2 Rainfall	50mm (2in) / hr-30 min	SLR**=4.78
	100mm (4in) / hr-30 min	SLR**=8.03
	150mm (6in) / hr-30 min	SLR**=13.49
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.08 lb/ft ²
ECTC Method 4 Germination	Top soil; Fescue; 21 day incubation	214% improvement
*Bench scale tests should not be used for design purposes.		
**Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor		
***The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO		

Slope Performance Design Values*:

Property	Test Method	Value	
Manning's N	Calculated	0.015	
C-Factors ASTM D6459			
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1
< 50 ft (15 m)	0.017	0.028	0.080
50 ft – 100 ft	0.031	0.059	0.125
>100 ft (30 m)	0.080	0.090	0.170
*Large-Scale Results obtained by 3 rd Party GAI Accredited Independent Laboratory			

Channel Performance Design Values*:

Property	Test Method	Value
Unvegetated Shear Stress	ASTM D 6460	2.60 lbs/ft ² (125 Pa)
Unvegetated Velocity	ASTM D 6460	8.0 ft/s (2.4 m/s)
Vegetated Shear Stress	NA	NA
Vegetated Velocity	NA	NA
*Large-Scale Results obtained by 3 rd Party GAI Accredited Independent Laboratory		

