



look for our FSC® certified products!

## SUPERIOR MASKING TAPE

Superior Performance Masking Tape made of saturated semi-creped fluo yellow paper, ideal for automotive applications and outdoor use. UV-resistant, waterproof, and with enhanced adhesion for immediate grip even on irregular surfaces. Suitable for thick coatings and resistant to temperatures up to 248°F (120°C) for 60 minutes. Suggested removal time: 14 days outdoor and 15 days indoor. FSC®-certified product available upon request.

**Backing:** Saturated Semi-Crepe Paper

**Adhesive:** Natural rubber

**Available colors:** fluo yellow

**Temperature resistance:** up to 248°F (120°C)/1h

**Waterproof:** yes

**UVR:** yes

TECHNICAL DATA	METRIC UNIT	IMPERIAL UNIT	TEST METHOD
<b>Total Thickness</b>	0.147mm	5.79mils	ASTM D3652/PSTC-133
<b>Adhesion To Steel</b>	5.9 N/25mm	21.2 oz/in	ASTM D3330/PSTC-101
<b>Tensile Strength</b>	91 N/25mm	21 lbs/in	ASTM D3759/PSTC-131
<b>Elongation at Breakage</b>	7%	7%	ASTM D3759/PSTC-131
<b>Rolling Ball Tack</b>	≤ 3 cm	≤ 1.18 in	ASTM D3121/PSTC-6

AVAILABLE MEASURES	HAND
<b>WIDTH - mm</b>	12 / 18 / 24 / 36 / 48 / 72
<b>WIDTH - in</b>	0.5 / 0.7 / 0.9 / 1.4 / 1.9 / 2.8
<b>LENGTH - m</b>	55
<b>LENGTH - yd</b>	60

All values provided are typical and do not constitute a guarantee of accuracy, or performance. Applications described are for reference only. Users must evaluate product suitability through testing under actual conditions of use, or otherwise. Proper adhesion require that surfaces be clean, dry and free of grease, oil or other contaminants. Liability is limited to the product's purchase price, consequential damages are excluded. We reserve the right to make changes without obligation in our products and publications.

**Storage & Shelf Life:**

Store in original packaging, in a cool, dry place (<65% RH) between 15-25°C (59-77°F), away from direct sunlight. Converted rolls have an expected shelf life of up to 12 months from the date of shipment. For jumbo rolls, the same shelf life applies; however, it is recommended to convert them within 6 months from shipment.