



Model Specification for Installation of Tekcem 212+ Leveller onto Sand and Cement Screed / Cement-Based Flowing Screed Using one Coat of Tekprime (Bonded System)

1. Substrate Requirements

Substrate Type:

Sand and cement screed or cement-based flowing screed suitable for bonded self-levelling systems.

Minimum Compressive Strength:

25 MPa.

Condition:

- Structurally sound, stable, and free from movement.
 - All cracks and surface defects repaired to achieve a flush, stable surface.
 - Free from laitance, dust, oil, grease, curing agents, and other contaminants.
 - Dry, with surface relative humidity $\leq 75\%$ (BS 8203).
 - Flat and level; significant deviations to be corrected prior to application.
-

2. Mechanical Surface Preparation

Method:

Mechanically abrade the surface using vacuum-assisted shot blasting, grinding, or equivalent to remove surface laitance and expose a clean, open texture.

Cleaning:

Remove all dust and debris using industrial vacuum equipment.

Moisture Testing:

Confirm surface RH $\leq 75\%$. If readings are higher, install a suitable moisture-tolerant surface DPM before priming.

3. Primer Application (Two Coats Tekprime)

Primer:

Tekcem Tekprime.

Dilution Ratio:

3 parts clean water : 1 part Tekprime (3:1).

**Coat 1:**

Apply the first diluted coat uniformly using a roller, soft broom, or squeegee. Allow to fully dry and film-form before applying the second coat (minimum 1 hour between coats depending on site conditions).

Coverage:

Approx. 170 m² per 5 litres of Tekprime at 3:1 dilution (per coat, subject to substrate porosity).

Conditions:

Do not apply primer if substrate or ambient temperature is below 5 °C or above 30 °C. Maintain RH below 75 % during curing.

4. Tekcem 212+ Leveller Specification

Product:

Tekcem 212+ Leveller – fast-setting, cement-based, protein-free, shrinkage-compensated self-levelling compound.

Water Addition:

5.8 – 6.0 litres per 25 kg unit.

Do not exceed 6 litres, as excess water can reduce strength and extend drying times.

Properties:

- Working time: 20–30 minutes @ 20 °C
- Light foot traffic: ~2 hours @ 20 °C
- Tile installation: after 3 hours @ 3 mm
- Resilient finishes: after 4 hours @ 3 mm
- Compressive strength (28 days): > 22 N/mm²
- Flexural strength (28 days): > 5 N/mm²

Thickness Guidelines (Bonded Systems):

Minimum 2 mm, maximum 12 mm in a single application.

For thicker applications, apply in multiple layers, priming between coats.

5. Screed Application

Mixing:

Add powder slowly to clean water while mixing with a slow-speed drill and paddle, or a suitable screed pump.

Mix until homogeneous and lump-free. Allow to stand 2 minutes, remix, and apply immediately.

Use each batch within 20–30 minutes of mixing.

**Placement:**

Pour or pump the leveller onto the primed substrate. Spread using a steel trowel to the required thickness and finish with a spiked roller to remove trapped air.

Environmental Conditions:

Substrate temperature 5–30 °C; ambient RH < 75 %.

6. Post-Installation

Drying & Overlay:

- Light foot traffic: ~2 hours @ 20 °C
- Tiled finishes: after 3 hours @ 3 mm
- Resilient finishes: after 4 hours @ 3 mm
- Ensure the screed is suitably dry for the intended floor finish.

Drying Guidance:

At 3 mm thickness, typically dry within 3–4 hours under good ventilation.

Low temperatures or high humidity will extend drying time.

Always test surface RH before installing sensitive finishes.

Curing:

No curing membrane is required; however, avoid rapid drying caused by direct heat or strong airflow.

Access:

Light traffic after 2–3 hours; full traffic after 24 hours.

7. Limitations

- Do not apply below 5 °C or above 30 °C.
- Not suitable for areas subject to permanent water immersion.
- Ensure substrate moisture ≤ 75 % RH before application.
- Always follow Tekcem's guidance on priming and substrate preparation for optimum bond strength.

8. Disclaimer

The information provided in this specification is based on Tekcem's experience and current knowledge and is given in good faith to assist in specifying the installation of Tekcem products. It does not replace the need for appropriate design, professional judgement, and proper site evaluation. Tekcem Ltd accepts no liability for the improper use of its products or deviation from the recommended guidelines.

Site conditions, working methods, substrate types, and application techniques can all vary significantly and are beyond Tekcem's control. Therefore, it is the responsibility of the contractor and/or installer to ensure that the products are suitable for the specific conditions of each individual project.

This specification does not relieve the user of the responsibility to carry out appropriate checks, tests, and quality assurance procedures prior to and during application.

Doc Ref - Tekcem 212+ _Tekprime 1 coat_Screed_May 2025 _R1