

No.: XMIN2211009395CM

Date: Dec 09, 2022

Page: 1 of 4



CUSTOMER NAME: EVERLASTING BASE SDN BHD

ADDRESS: LOT3623-3626 TAMAN PERINDUSTRIAN JASIN ,77200 BEMBAN,

MELAKA, MALAYSIA

Sample Name : SPC6512-3

Manufacturer : EVERLASTING BASE SDN BHD

Material and Mark : SPC

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : GZMR221103727401

Date of Receipt : Nov 23, 2022
Testing Start Date : Nov 23, 2022
Testing End Date : Dec 05, 2022

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services Co., Ltd Xiamen Branch Testing Center

Bryan Hong

Authorized signatory





No.: XMIN2211009395CM


Date: Dec 09, 2022

Page: 2 of 4

Summary of Results:

No.	Test Item	Test Method	Result
	Determination of the Burning		
1	Behavior Using a Radiant Heat	ASTM E648-19a ^{€1}	Class I
	Source		

Original Sample Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions-and-Conditions-and-C

| No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 | t (86-592) 5765857 | f (86-592) 5765380 | www.sgsgroup.com.cn |
中国・福建・厦门・火炬(翔安)产业区翔虹路31号 | 邮编:361101 | t (86-592) 5765857 | f (86-592) 5765380 | e sgs.china@sgs.com



No.: XMIN2211009395CM

Date: Dec 09, 2022

Page: 3 of 4

Test item: Determination of the Burning Behavior Using a Radiant Heat Source

Sample Description: Floor

Test Method: ASTM E648-19a^{€1}

Test condition:

Specimen: 1050mm×230mm×5.0mm

Flame application time: 5min

Test result:

Specimen No.	Furthest extent of spread of flame, mm	Critical heat flux, watts/cm ²	
1	70	≥ 1.0	
2	60	≥ 1.0	
3	60	≥ 1.0	
Average	60	≥ 1.0	

Note:

- 1. Test specimens were cut from sample.
- 2. Specimens that do not ignite or which spread flame less than 100 mm have a critical heat flux \geq 1.0 W/cm2.
- 3. The grain surface was faced to the flame.
- 4. Observations of the burning characteristics: Charring
- 5. ASTM E648-19a^{£1} is solely a test procedure and, as such, has no specific pass/fail criteria of its own. Table 1 specification criteria are cited for reference purposes only, and may or may not apply to this tested product. International Building Code, Chapter 8, Interior Finishes, Section 804 "INTERIOR FLOOR FINISH", was classified in accordance with ASTM E648-19a^{£1} or NFPA 253. Such interior finish materials shall be grouped in table 1 classes in accordance with their critical heat flux ratings.

The classifications are as follows:

Ratings	Class I	Class II
Critical heat flux, watts/cm ²	≥0.45	≥0.22

Conclusion: Met the requirement of Class I

Statement: The test results relate to the behavior of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic Focuments at <a href="http://www.sgs.com/en/Terms-and-Conditions-and-Conditions-and

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgsgroup.com.c 中国•福建•厦门•火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.co



No.: XMIN2211009395CM

Date: Dec 09, 2022

Page: 4 of 4

Test Photo:



During Test





Equipment Information:

Fauinment	Model	Equipment No.	Calibration date	Next Calibration
Equipment				date
Flooring Radiant	FPR	GZMR-PL-E227	2022-05-24	2023-05-23
Panel Tester	111X			

Note: The above test project/method was carried out by subcontractors.

********** End of report**********



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions, aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fulles tent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765830 www.sgsgroup.com.cn 中国•福建•厦门•火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765860 e sgs.china@sgs.com