





NANOBRAND


NB-GSPU-40-CTAC-1

40nm Ultra-monodisperse Gold Nano-Spheres

CTAC
CAS 112-02-7



Diameter (TEM):	40.01 ± 0.21 nm
Coefficient of polydispersity:	0.51%
Mass of single particle:	6.472 E-13 mg
Surface of single particle:	5029 nm ²
Volume of single particle:	3.354 E+4 nm ³
Particles concentration:	7.73 E+10 particles/ml
Molar particles concentration:	0.0129 nM
Surface area (TEM):	7.77 m ² /g
Surface to volume ratio:	0.15 nm ⁻¹
Mass of gold:	50 µg/ml
Hydrodynamic diameter (DLS):	54.07 nm
Zeta-potential:	+34.5 mV
pH of the solution:	6 - 7
Particle surface:	CTAC
Solvent:	Milli-Q water (18.1 MΩ-cm)



Instrumentation used for characterization

Diameter and size distribution:	Transmission Electron Microscope Thermo Scientific TALOS F200X
Mass concentration:	PerkinElmer NexION 2000P+ ICP-MS
Spectral properties:	PerkinElmer Lambda 365+ UV-Visible Spectrophotometer
Hydrodynamic Diameter and Zeta Potential:	Malvern Zetasizer



Shake before use. Store at 18-25°C away from light. DO NOT FREEZE.




NANOBRAND

NB-GSPU-40-CTAC-1

40nm Ultra-monodisperse Gold Nano-Spheres



Optical Properties



Size Distribution

