

## SilverNanoDispersion4K Chitosan Technical Data Sheet:

<u>Appearance</u>Lightyellowtransparent/iscousliquid.

<u>Ingredient</u>sConcentrated Colloidal Silver Solutation4000ppm(0.4wt%) of silver, manufacture from silver salt USP graated stabilized by chitosacontainssilver nanoparticles

- Ø Cost efficient
- Ø Stable
- Ø Good compatibility with a variety of ingredients
- Ø Easy to dose and formulate
- Ø No added colors or scents
- Ø No added parabenshenols, or quaternary ammonium compounds

<u>Usage Guideline</u>s is a concentrated solution. It should be added to the products in DILUTED form according to the anticipated concentration of silver in your final products and to the desired effect.

Because of different national regulations for preservatives and antimicrobials, used in cosmetics, home care and industry, the local registration and formulation rules should be applied for your final product.

Solubility: Highly soluble in water. Use DI water without chlorine ONLY.

Shelf life2 years, properly stored. Protect from the direct sunlight. Do not freeze.


<u>Documentationeach</u> lot is accompanied with COA, which includes measured concentrations of silver another firmation of absence host around the silver another impurities.


Instrumentation used for characterization	
Diameter and size distribution:	Transmission Electron Microscope HITACHIDD
Mass concentration:	PerkinElmerNexION 2000P+ IGPMS
Spectral properties:	Thermo Scientific Evolution 220Vib/ble Spectrophotomete
Hydrodynamic Diameter and Zeta Poten	MalvernZetasizerNANO-ZS






Mass of silver:	4g/L=0.4wt%=4000ppm
pH of the solution:	5.0 - 5.5
Particle surface:	Chitosan
Chitosan concentratio	0.25wt%
Peak wavelength:	423.5nm
OD:	0.58
Zeta-potential:	34.4mV
Solvent:	Milli-Q water(18.1 MK -cm)







First Colloidal 230 rue Bernaßdlleau, suite 127 Laval, Quebec H7V 4A9 Canada

firstcolloidal.com

<u>sales@firstcolloidal.c</u>om 4566860111